

Technicure® IPDU-8

Description:

Technicure® IPDU-8, N-3-(dimethylamino) carbonylamino methyl-3,5,5-trimethylcyclohexyl-N,N-dimethyl-urea, is a substituted urea. It is used as a dicyandiamide (DICY) accelerator in one-component epoxy resin based formulations. Typically the product is used with epoxy resin and dicyandiamide between 1-3 phr. The loading level of an accelerator will provide balance of low temperature reactivity and formulation shelf stability.

Among all substituted ureas as DICY cure accelerators, IPDU-8 offers the most latency.

Advantages:

- Good formulation shelf stability
- Moderate glass transition temperature
- Excellent adhesion to a variety of substrates

Typical Applications:

- One-component paste and film adhesives for automotive and aerospace applications
- Composites such as pre-pregs
- Powder coatings

Handling Precautions:

Refer to the product Safety Data Sheet

Typical Properties:

Appearance:	Off White powder
Average Particle Size:	>80% less than 44 micron
Melting point:	190 - 210°C
Assay:	98% minimum
Moisture content:	<0.7%

Recommended use level with

Epoxy resin (EEW=190):	1-3 PHR with 3-8 PHR of DICY
------------------------	------------------------------

Typical Formulations (by wt.):

Liquid epoxy resin (EEW=190)	100	100
Technicure® D-10 ¹	8	8
Technicure® IPDU-8	1	3
Fumed silica (H 200U) ²	1	1

Reactivity by DSC³

Onset Temp., °C	151	144
Peak Temp., °C	162	155
Heat of Reaction, J/gm	298	266

Glass Transition Temperature⁴, °C

151	151
-----	-----

1. Dicy – Product of ACCI Specialty Materials
2. Fumed silica – Product of OCI Company Ltd.
3. 10°C/min. scan rate
4. By DMA, after 60 minutes cure at 140°C

A&C Catalysts, Inc.

1600 W. Blancke St. Linden, NJ 07036 Tel: (908) 474-9393 Fax: (908) 474-9388 www.ac-catalysts.com

A&C Catalysts, Inc. is not responsible for the use of the information, and no warranty is made of the merchantability or fitness of any product. Purchasers of any product must determine whether the product is acceptable for their particular purpose, under their own operation conditions. Nothing herein waves any of A&C Catalysts Inc. conditions of sale. Nothing herein shall imply the nonexistence of any relevant patents or to constitute permission, inducement, or recommendation to practice any invention covered by any patent, without authority from its owner

Supplemental Technical Information:


Three one-part formulations (Table 1) containing Technicure® IPDU-8 were prepared to evaluate the effect of increasing level of the product on gel time at different temperatures.

Data in Table 1 shows that as the loading level of Technicure® IPDU-8 increases the gel time decreases. The effect of loading level is more pronounced at higher temperature.

Table 1. Formulations (by wt.) and gel time

Liquid Epoxy resin (EEW=190)	100	100	100
Technicure® D-10	8	8	8
Technicure® IPDU-8	1	2	3
Fumed silica (H 200U)	1	1	1
Gel time ¹ , minutes			
@ 120°C	30.5	23.8	20.1
@130°C	17.1	13.1	8.6

1. Sunshine gel timer



A&C Catalysts, Inc.

1600 W. Blancke St. Linden, NJ 07036 Tel: (908) 474-9393 Fax: (908) 474-9388 www.ac-catalysts.com

A&C Catalysts, Inc. is not responsible for the use of the information, and no warranty is made of the merchantability or fitness of any product. Purchasers of any product must determine whether the product is acceptable for their particular purpose, under their own operation conditions. Nothing herein waves any of A&C Catalysts Inc. conditions of sale. Nothing herein shall imply the nonexistence of any relevant patents or to constitute permission, inducement, or recommendation to practice any invention covered by any patent, without authority from its owner