

DUROFTAL® VPE 6117

TYPE

Aliphatic polyester resin

FORM OF DELIVERY (f.o.d.)

100 %

PRODUCT DATA

Determined per batch:

Dynamic Viscosity DIN EN ISO 3219 dynamic viscosity (25 1/s; 23 °C)	[mPa.s]	6000 - 12000
---	---------	--------------

Colour Scale (Hazen) DIN EN ISO 6271-1 Hazen colour value		< 80
--	--	------

Acid Value DIN EN ISO 2114 acid value (solids)	[mg KOH/g]	< 10
--	------------	------

Non-Volatile Matter DIN 55671 non-volatile matter (120 °C; 5 min)	[%]	> 96
---	-----	------

Not continually determined:

Hydroxyl Value DIN 53240 hydroxyl value (nfA)	[mg KOH/g]	120 - 140
---	------------	-----------

Density (Liquids) DIN EN ISO 2811-2 density approx. (20 °C)	[g/cm³]	1,11
--	---------	------

Flash Point (Pensky-Martens) DIN EN ISO 2719 flash point	[°C]	> 100
---	------	-------

SPECIAL PROPERTIES AND USE

As a combination partner for other resins, Duroftal VPE 6117 contributes to increased solids content of the paint and to improved build, gloss and flexibility of the paint film.

It may be used in solvent based or in water based paint formulations, either in 1-pack enamels or in polyisocyanate crosslinking 2-pack systems.

PROCESSING

At additions of at least 10 % Duroftal VPE 6117 (based on co-binder solids), a significant improvement in the appearance of the coatings is usually achieved. Compatibility of the resin blend and stability of the paint have to be checked, however. The marked plastifying effect of Duroftal VPE 6117 should also be taken in to consideration.

Duroftal VPE 6117 is insoluble in water. Therefore, when used in waterborne paints, it has to be emulsified by the other paint components in the course of the paint manufacturing process.

STORAGE

At temperatures up to 25 °C storage stability packed in original containers amounts to at least 730 days.

3.0/17.07.2013 (replaces all previous versions)

• Worldwide Contact Info: www.allnex.com •

Disclaimer: Allnex Group companies ("Allnex") decline any liability with respect to the use made by anyone of the information contained herein. The information contained herein represents Allnex's best knowledge thereon without constituting any express or implied guarantee or warranty of any kind (including, but not limited to, regarding the accuracy, the completeness or relevance of the data set out herein). Nothing contained herein shall be construed as conferring any license or right under any patent or other intellectual property rights of Allnex or of any third party. The information relating to the products is given for information purposes only. No guarantee or warranty is provided that the product and/or information is adapted for any specific use, performance or result and that product and/or information do not infringe any Allnex and/or third party intellectual property rights. The user should perform its own tests to determine the suitability for a particular purpose. The final choice of use of a product and/or information as well as the investigation of any possible violation of intellectual property rights of Allnex and/or third parties remains the sole responsibility of the user.

© 2013 Allnex Belgium SA. All Rights Reserved

Notice: Trademarks indicated with the ®, ™ or * are registered, unregistered or pending trademarks of Allnex Belgium SA or its directly or indirectly affiliated Allnex Group companies.