

MACRYNAL[®] SM 2810/75BAC

TYPE

Hydroxy functional acrylic resin designed for crosslinking with polyisocyanates

Average hydroxyl content (solid resin)

approx. 4.2 %

FORM OF DELIVERY (f.o.d.)

75 % in butyl acetate (75BAC)

PRODUCT DATA

Determined per batch:

Dynamic Viscosity DIN EN ISO 3219
dynamic viscosity [mPa.s] 4500 - 6000
(25 1/s; 23 °C)

Colour Scale (Hazen) DIN EN ISO 6271-1
Hazen colour value <= 100

Hydroxyl Value (cat.) DIN EN ISO 4629
hydroxyl value [mg KOH/g] 130 - 150
(solids)

Non-Volatile Matter DIN EN ISO 3251
non-volatile matter [%] 73 - 77
(1 h; 125 °C; 2 g; EAC)

Not continually determined:

Density (Liquids) DIN EN ISO 2811-2
density [g/cm³] 1,04
approx.
(20 °C)

Flash Point DIN EN ISO 1523
flash point [°C] 28
approx.

SPECIAL PROPERTIES

Macrynal SM 2810 is meant for high solids two pack coatings with outstanding overall properties, such as chemical resistance, mechanical properties and outdoor stability.

SUGGESTED USES

In combination with aliphatic polyisocyanates, such as Desmodur N 3390, Macrynal SM 2810 is used for air-drying and forced drying high-solids two pack coatings. The principal application areas are car refinish, ACE (agricultural, construction and earthmoving equipment) as well as high quality industrial coatings. Paints based on Macrynal SM 2810 display a low content of volatile organic compounds (VOC).

PROCESSING

As a two pack system Macrynal SM 2810 must be combined with polyisocyanates. Dried at room temperature, the coatings reach their optimum properties after 10 to 12 days. If forced dried, 30 min at 80 °C is sufficient for complete curing. The addition of cellulose acetobutyrate speeds up physical drying.

Curing with polyisocyanates

Based on 100 % conversion of reactive groups the following equation can be used to calculate the quantity of polyisocyanate needed for crosslinking 100 parts Macrynal SM 2810 (on solids):

$$\text{polyisocyanate (f.o.d.)} = \frac{42 \times 100 \times \text{OH\% (solid resin)}}{17 \times \text{NCO\% (f.o.d.)}}$$

42 = molecular weight of the NCO group

17 = molecular weight of the OH group

To ensure that optimal properties are obtained it is necessary to have complete crosslinking. Over- or under-crosslinking is possible within certain limits.

Catalysis

Drying can be accelerated by the addition of suitable catalysts, like dibutyl tin dilaurate (0.2 - 0.5 % of a 1 % solution, based on solid resin), in combination with amines like diethyl amino ethanol (approx. 0.2 %, based on solid resin). Potlife is thereby reduced, however.

STORAGE

At temperatures up to 25 °C storage stability packed in original containers amounts to at least 730 days.

DISTINGUISHING FEATURES

Compared to Macrynal SM 565, formulations based on Macrynal SM 2810 lead to a higher solid content as well as better drying speed.

5.0/17.07.2013 (replaces all previous versions)

• Worldwide Contact Info: www.allnex.com •

Disclaimer: Allnex Group companies ("Allnex") decline any liability with respect to the use made by anyone of the information contained herein. The information contained herein represents Allnex's best knowledge thereon without constituting any express or implied guarantee or warranty of any kind (including, but not limited to, regarding the accuracy, the completeness or relevance of the data set out herein). Nothing contained herein shall be construed as conferring any license or right under any patent or other intellectual property rights of Allnex or of any third party. The information relating to the products is given for information purposes only. No guarantee or warranty is provided that the product and/or information is adapted for any specific use, performance or result and that product and/or information do not infringe any Allnex and/or third party intellectual property rights. The user should perform its own tests to determine the suitability for a particular purpose. The final choice of use of a product and/or information as well as the investigation of any possible violation of intellectual property rights of Allnex and/or third parties remains the sole responsibility of the user.

© 2013 Allnex Belgium SA. All Rights Reserved

Notice: Trademarks indicated with the ®, ™ or * are registered, unregistered or pending trademarks of Allnex Belgium SA or its directly or indirectly affiliated Allnex Group companies.