

# MACRYNAL<sup>®</sup> SM 2815/70BAC

## PRELIMINARY PRODUCT INFORMATION

### TYPE

Hydroxyfunctional, acrylic modified polyester; cross-linkable with polyisocyanates for the production of high solids lacquers

### FORM OF DELIVERY (f.o.d.)

70 % in butyl acetate (70BAC)

## DEVELOPMENT PRODUCT

This product is serving for trial purposes only. Deviations which might occur during transfer into manufacturing in a commercial scale are possible and do not constitute any material defect.

Average hydroxyl content (solid resin)

approx. 5.5 %

## TENTATIVE PRODUCT DATA

Determined per batch:

Dynamic Viscosity DIN EN ISO 3219 dynamic viscosity (25 1/s; 23 °C)	[mPa.s]	800 - 1600
---	---------	------------

Colour Scale (Hazen) DIN EN ISO 6271-1 Hazen colour value		<= 100
--	--	--------

Hydroxyl Value DIN EN ISO 4629 (VLN 283) hydroxyl value (solids)	[mg KOH/g]	170 - 190
--	------------	-----------

Non-Volatile Matter DIN EN ISO 3251 non-volatile matter (1 h; 125 °C; 2 g; EAC)	[%]	69 - 71
---	-----	---------

Not continually determined:

Density (Liquids) DIN EN ISO 2811-2 density ca. (20 °C)	[g/cm <sup>3</sup> ]	1,05
--	----------------------	------

Flash Point DIN EN ISO 1523 flash point ca.	[°C]	26
---	------	----

## SPECIAL PROPERTIES AND USE

Macrynal SM 2815, in combination with aliphathic polyisocyanates, produces high quality high solids 2-component lacquers. One specific strength of the product is the fast through-drying capability even at ambient cure conditions.

Coatings based on Macrynal SM 2815 show properties like:

- very good balance of hardness and flexibility
- very good resistance towards solvents
- very good weathering stability

Macrynal SM 2815, in combination with aliphathic polyisocyanates, is recommended for high quality 2-component lacquers with low contents of volatile organic compounds (VOC). Due to the outlined properties Macrynal SM 2815 is especially suited for topcoats and direct-to-metal monocoats in demanding outdoor applications.

## STORAGE

At temperatures up to 25 °C storage stability packed in original containers amounts to at least 730 days.

## DISTINGUISHING FEATURES

In comparison to Macrynal VSM 2805 coatings based on Macrynal SM 2815 show shorter surface- and through-dry times as well as higher end hardness and better chemical resistance, on the contrary the achievable paint solids is somewhat lower.

## REMARK:

Data contained in this publication are based on careful investigations (and are intended for information only). Due to scale up of this product there is not yet sufficient experience concerning serial production. We can therefore not exclude, that based on future knowledge product data and other indicated properties in upcoming Technical Data Sheets will be subject to change. We reserve the right to leave the product name unchanged, even if product data or other indicated properties will vary from the present product info. Regardless of the data contained in this publication any user is obliged to carry out tests under his own responsibility as to the suitability of the product for a particular use and to investigate the possible violation of industrial property rights of third parties. Information is therefore not binding and cannot be construed as guaranteeing specific properties of products. We apply our General Sales Conditions.

2.0/18.04.2016 ( replaces 1.0/07.01.2015 )

• Worldwide Contact Info: [www.allnex.com](http://www.allnex.com) •

Disclaimer: Allnex Group companies (\*Allnex\*) decline any liability with respect to the use made by anyone of the information contained herein. The information contained herein represents Allnex's best knowledge thereon without constituting any express or implied guarantee or warranty of any kind (including, but not limited to, regarding the accuracy, the completeness or relevance of the data set out herein). Nothing contained herein shall be construed as conferring any license or right under any patent or other intellectual property rights of Allnex or of any third party. The information relating to the products is given for information purposes only. No guarantee or warranty is provided that the product and/or information is adapted for any specific use, performance or result and that product and/or information do not infringe any Allnex and/or third party intellectual property rights. The user should perform its own tests to determine the suitability for a particular purpose. The final choice of use of a product and/or information as well as the investigation of any possible violation of intellectual property rights of Allnex and/or third parties remains the sole responsibility of the user.  
© 2013 Allnex Belgium SA. All Rights Reserved

Notice: Trademarks indicated with the ®, ™ or \* are registered, unregistered or pending trademarks of Allnex Belgium SA or its directly or indirectly affiliated Allnex Group companies.