

# MACRYNAL<sup>®</sup> SM 510n/60XMPAC

## TYPE

Hydroxy functional acrylic resin designed for crosslinking with polyisocyanates

## SPECIAL PROPERTIES AND USE

At room temperature drying or forced drying two-pack systems with high gloss, excellent mechanical properties, superior outdoor stability and chemical resistance, in particular for automotive repair topcoats or clearcoats.

## FORM OF DELIVERY (f.o.d.)

60 % in xylene / methoxypropyl acetate (60XMPAC)  
(xylene : methoxypropyl acetate = 2 : 1)

Average hydroxyl content (solid resin)

approx. 4.5 %

## DILUTABILITY

white spirit	»	methyl ethyl ketone	}
toluene	}	methyl isobutyl ketone	}
xylene	}	methoxypropyl acetate	}
solvent naphtha 150/180	½	ethyl acetate	}
acetone	}	butyl acetate	}

} = unlimited dilutability

½ = substantial dilutability

¾ = limited dilutability

» = very limited or no dilutability

## PRODUCT DATA

Determined per batch:

Dynamic Viscosity DIN EN ISO 3219  
dynamic viscosity [mPa.s] 2500 - 4000  
(25 1/s; 23 °C)

Colour Scale (Hazen) DIN EN ISO 6271-1  
Hazen colour value <= 60

Acid Value DIN EN ISO 2114  
acid value [mg KOH/g] 5 - 10  
(solids)

Hydroxyl Value (cat.) DIN EN ISO 4629  
hydroxyl value [mg KOH/g] 140 - 160  
(solids)

Non-Volatile Matter DIN EN ISO 3251  
non-volatile matter [%] 58 - 62  
(1 h; 125 °C; 2 g; EAC)

Not continually determined:

Density (Liquids) DIN EN ISO 2811-2  
density [g/cm³] 1,03  
approx.  
(20 °C)

Flash Point DIN EN ISO 1523  
flash point [°C] 27  
approx.

## COMPATIBILITY

% Macrynal SM 510n	90	75	50	25	10
% other binder	10	25	50	75	90
Alkyd resins					
Vialkyd AC 290, AC 451n	}	}	}	}	}
Vialkyd AF 342	»	»	»	}	}
Vialkyd AN 950	}	}	}	}	}
Acrylic resins					
Viacryl SC 121	»	»	»	»	»
Viacryl SC 370	}	}	}	}	}
Macrynal SM 510, SM 513, SM 515, SM 516	}	}	}	}	}
Macrynal SM 500, SM 540	»	»	»	»	»
Macrynal SM 548	}	}	»	»	»
Polyisocyanates					
Desmodur L, N	}	}	}	}	}
Beckocoat PU 428, PU 432	}	}	}	}	}
Other binders					
Beckopox EP 140	}	}	}	}	»
Beckopox EP 301	}	}	}	}	}
Hostaflex CM 158	}	}	}	}	}
Hostaflex CM 620	»	»	»	»	»
Ucar solution vinyl resin VAGH	}	}	}	}	}
CAB-551-0.2	}	»	»	»	}
CAB-381-0.1	»	»	»	»	}
Nitrocellulose 24 E	}	}	}	}	}

} = definite compatibility

» = very limited or no compatibility

## SUGGESTED USES

In combination with aliphatic polyisocyanates Macrynal SM 510n is recommended for air-drying or forced drying two-pack systems. The principal application field is automotive refinishing (topcoats and clearcoats).

## PROCESSING

As a two-pack system Macrynal SM 510n must be combined with polyisocyanates. Dried at room temperature, the coatings reach their optimum properties after 10 to 12 days. If forced dried, 30 min at 80 °C is sufficient for complete curing.

### Curing with polyisocyanates

Based on 100 % conversion of reactive groups the following equation can be used to calculate the quantity of polyisocyanate needed for crosslinking 100 parts Macrynal SM 510n (on solids):

$$\text{polyisocyanate (f.o.d.)} = \frac{42 \times 100 \times \text{OH\% (solid resin)}}{17 \times \text{NCO\% (f.o.d.)}}$$

42 = molecular weight of the NCO group

17 = molecular weight of the OH group

To ensure that optimal properties are obtained it is necessary to have complete crosslinking. Over - or under - crosslinking is possible within certain limits.

### Catalysis

Drying can be accelerated by the addition of suitable catalysts, like dibutyl tin dilaurate (0.2 - 0.5 % of a 1 % solution, based on solid resin), in combination with amines like diethyl amino ethanol (ca. 0.2 %, based on solid resin). Potlife is thereby reduced, however.

### Pigmentation

Inert pigments and extenders are suitable for pigmentation. Care should be taken the material selected is free of water. Suitability should be established by preliminary testing.

### Dilution

Suitable diluents are butyl acetate, methyl isobutyl ketone, 2-methoxypropyl acetate, xylene and mixtures of these solvents. Anhydrous solvents as well as solvents free of hydroxy functional groups should be used in the presence of isocyanates.

## STORAGE

At temperatures up to 25 °C storage stability packed in original containers amounts to at least 730 days.

## DISTINGUISHING FEATURES

Compared to Macrynal SM 513 Macrynal SM 510n has a higher hydroxyl content. Therefore, higher crosslinking density and better outdoor stability are achieved.

### Producers:

Desmodur N, L (Bayer)

Ucar solution vinyl resin VAGH (Union Carbide)

CAB-551-0.2, CAB-381-0.1 (Eastman)

3.0/17.07.2013 ( replaces all previous versions )

• Worldwide Contact Info: [www.allnex.com](http://www.allnex.com) •

Disclaimer: Allnex Group companies ("Allnex") decline any liability with respect to the use made by anyone of the information contained herein. The information contained herein represents Allnex's best knowledge thereon without constituting any express or implied guarantee or warranty of any kind (including, but not limited to, regarding the accuracy, the completeness or relevance of the data set out herein). Nothing contained herein shall be construed as conferring any license or right under any patent or other intellectual property rights of Allnex or of any third party. The information relating to the products is given for information purposes only. No guarantee or warranty is provided that the product and/or information is adapted for any specific use, performance or result and that product and/or information do not infringe any Allnex and/or third party intellectual property rights. The user should perform its own tests to determine the suitability for a particular purpose. The final choice of use of a product and/or information as well as the investigation of any possible violation of intellectual property rights of Allnex and/or third parties remains the sole responsibility of the user.

© 2013 Allnex Belgium SA. All Rights Reserved

Notice: Trademarks indicated with the ®, ™ or \* are registered, unregistered or pending trademarks of Allnex Belgium SA or its directly or indirectly affiliated Allnex Group companies.