

MACRYNAL[®] VSM 2570/70BAC

TYPE

Hydroxy functional acrylic resin; cross-linkable with polyisocyanates for high-solids lacquers

Average hydroxyl content (solid resin)

approx. 2.4 %

FORM OF DELIVERY (f.o.d.)

70 % in butyl acetate (70BAC)

OH equivalent weight (f.o.d.)

approx. 1000 g

PRODUCT DATA

Determined per batch:

Dynamic Viscosity DIN EN ISO 3219
dynamic viscosity [mPa.s] 2200 - 3800
(25 1/s; 23 °C)

Colour Scale (Hazen) DIN EN ISO 6271-1
Hazen colour value <= 80

Hydroxyl Value (cat.) DIN EN ISO 4629
hydroxyl value [mg KOH/g] 70 - 90
(solids)

Non-Volatile Matter DIN EN ISO 3251
non-volatile matter [%] 68 - 72
(1 h; 125 °C; 2 g; EAC)

Not continually determined:

Colour / Appearance VLN 250
colour colourless
appearance clear

Density (Liquids) DIN EN ISO 2811-2
density [g/cm³] 1,04
approx.
(20 °C)

Flash Point DIN EN ISO 1523
flash point [°C] 26
approx.

SPECIAL PROPERTIES

- High solids content at application viscosity
- Good drying speed
- Good adhesion to metals
- Very good mechanical properties
- Good gloss and good outdoor durability

SUGGESTED USES

Macrynal VSM 2570 is a hydroxy functional acrylic resin cross-linkable with aliphatic polyisocyanates to formulate air drying and forced drying 2-pack high solids coating systems.

In pigmented topcoats (pigment/binder = 1 : 1) a solids content of 65 % at application viscosity of 55 s (efflux time DIN EN ISO 2431, 4 mm, 23 °C) can be achieved.

To ensure that optimal properties are obtained it is necessary to have complete crosslinking. For stoichiometric (equivalent) crosslinking (NCO : OH = 1 : 1) approx. 100 parts per weight Macrynal VSM 2570 (f.o.d.) require approx. 21 parts per weight Desmodur N 3390 (Bayer).

Catalysis

Drying can be accelerated by addition of suitable catalysts like dibutyl tin dilaurate (0.2 - 0.5 % of a 1 % solution, based on solid resin) in combination with amines like diethyl amino ethanol (approx. 0.2 %, based on solid resin). Potlife is thereby reduced, however.

Dilution

Suitable diluents are butyl acetate, methyl isobutyl ketone, 2-methoxypropyl acetate or aromatic solvents like solvent naphtha 150/180. Anhydrous solvents as well as solvents free of hydroxy functional groups should be used in the presence of isocyanates.

Pigments

Inert pigments and extenders are suited for pigmentation. Pigments with basic surface treatment can act as additional catalyst and shorten the potlife even more.

Additives

To improve levelling Additol VXL 4930 is recommended. Additol VXL 6212 has proved to be an effective wetting agent.

STORAGE

At temperatures up to 25 °C storage stability packed in original containers amounts to at least 730 days.

DISTINGUISHING FEATURES

Compared to Macrynal SM 500, Macrynal VSM 2570 provides higher solids content and better outdoor durability.

4.0/17.07.2013 (replaces all previous versions)

• Worldwide Contact Info: www.allnex.com •

Disclaimer: Allnex Group companies ("Allnex") decline any liability with respect to the use made by anyone of the information contained herein. The information contained herein represents Allnex's best knowledge thereon without constituting any express or implied guarantee or warranty of any kind (including, but not limited to, regarding the accuracy, the completeness or relevance of the data set out herein). Nothing contained herein shall be construed as conferring any license or right under any patent or other intellectual property rights of Allnex or of any third party. The information relating to the products is given for information purposes only. No guarantee or warranty is provided that the product and/or information is adapted for any specific use, performance or result and that product and/or information do not infringe any Allnex and/or third party intellectual property rights. The user should perform its own tests to determine the suitability for a particular purpose. The final choice of use of a product and/or information as well as the investigation of any possible violation of intellectual property rights of Allnex and/or third parties remains the sole responsibility of the user.

© 2013 Allnex Belgium SA. All Rights Reserved

Notice: Trademarks indicated with the ®, ™ or * are registered, unregistered or pending trademarks of Allnex Belgium SA or its directly or indirectly affiliated Allnex Group companies.