

MACRYNAL[®] VSM 6299w/42WA

TYPE

Aqueous, hydroxy functional acrylic resin

Neutralization agent

1.3 % N,N-dimethylethanolamine, as salt

FORM OF DELIVERY (f.o.d.)

42 % in water (42WA)

Appearance

whitish

PRODUCT DATA

Determined per batch:

Dynamic Viscosity DIN EN ISO 3219 dynamic viscosity (10 1/s; 23 °C)	[mPa.s]	800 - 4000
---	---------	------------

pH-Value DIN ISO 976 pH-value (10 %)		7,0 - 8,5
--	--	-----------

Acid Value DIN EN ISO 2114 acid value (solids)	[mg KOH/g]	20 - 30
--	------------	---------

Non-Volatile Matter DIN EN ISO 3251 non-volatile matter (1 h; 125 °C; 1 g)	[%]	40,5 - 43,5
--	-----	-------------

Not continually determined:

Hydroxyl Value DIN 53240 hydroxyl value approx. (solids)	[mg KOH/g]	135
---	------------	-----

Density (Liquids) DIN EN ISO 2811-2 density approx. (20 °C)	[g/cm ³]	1,06
--	----------------------	------

Flash Point (Pensky-Martens) DIN EN ISO 2719 flash point	[°C]	>85
---	------	-----

SPECIAL PROPERTIES AND USE

In combination with water-emulsifiable polyisocyanates for high quality 2-pack-topcoats with excellent development of hardness at room temperature drying and very good gloss.

STORAGE

At temperatures up to 25 °C storage stability packed in original containers amounts to at least 180 days.

It is important to protect Macrynal VSM 6299w from frost; at low temperatures it has therefore to be stored under frostproof conditions.

Lowest storage temperature: + 1 °C

DISTINGUISHING FEATURES

Compared with Macrynal VSM 6285w, Macrynal VSM 6299w shows faster drying at room temperature and achieves substantially higher hardness of the final films.

4.0/17.07.2013 (replaces all previous versions)

• Worldwide Contact Info: www.allnex.com •

Disclaimer: Allnex Group companies (*Allnex*) decline any liability with respect to the use made by anyone of the information contained herein. The information contained herein represents Allnex's best knowledge thereon without constituting any express or implied guarantee or warranty of any kind (including, but not limited to, regarding the accuracy, the completeness or relevance of the data set out herein). Nothing contained herein shall be construed as conferring any license or right under any patent or other intellectual property rights of Allnex or of any third party. The information relating to the products is given for information purposes only. No guarantee or warranty is provided that the product and/or information is adapted for any specific use, performance or result and that product and/or information do not infringe any Allnex and/or third party intellectual property rights. The user should perform its own tests to determine the suitability for a particular purpose. The final choice of use of a product and/or information as well as the investigation of any possible violation of intellectual property rights of Allnex and/or third parties remains the sole responsibility of the user.
© 2013 Allnex Belgium SA. All Rights Reserved

Notice: Trademarks indicated with the ®, ™ or * are registered, unregistered or pending trademarks of Allnex Belgium SA or its directly or indirectly affiliated Allnex Group companies.