

RESYDROL[®] AY 6173w/45WA

TYPE

Air-drying, acrylic modified alkyd resin emulsion

Neutralization agent

0.6 % ammonia, as salt

FORM OF DELIVERY (f.o.d.)

 45 % in water (45WA)
 (containing also < 1 % n-butoxy propanol)

CONTENT OF FATTY ACIDS

approx. 33 % special vegetable fatty acids (as triglycerides)

PRODUCT DATA

Determined per batch:

Dynamic Viscosity DIN EN ISO 3219 dynamic viscosity (100 1/s; 23 °C)	[mPa.s]	300 - 1500
--	---------	------------

pH-Value DIN ISO 976 pH-value (10 %)		8,0 - 9,2
--	--	-----------

Non-Volatile Matter DIN 55671 non-volatile matter (120 °C; 5 min)	[%]	43,5 - 46,5
---	-----	-------------

Not continually determined:

Colour / Appearance VLN 250 colour appearance		light brown opaque
---	--	-----------------------

Non-Volatile Matter DIN EN ISO 3251 non-volatile matter (1 h; 125 °C; 1 g)	[%]	43,5 - 46,5
--	-----	-------------

Density (Liquids) DIN EN ISO 2811-2 density approx. (20 °C)	[g/cm ³]	1,05
--	----------------------	------

Flash Point (Pensky-Martens) DIN EN ISO 2719 flash point	[°C]	> 100
---	------	-------

SPECIAL PROPERTIES AND USES

Resydrol AY 6173w/45WA is designed for the production of air-drying, waterborne 1 pack primers. Primers based on this resin show quick drying, corrosion protection, good adhesion on various substrates and very good recoatability at any time.

Such paints show high built and mild odour.

Resydrol AY 6173w/45WA can also be used as sole binder or in combination with dispersions for the formulation of wood primers.

DILUTABILITY

Resydrol AY 6173w/45WA can be diluted with deionized water as much as desired. The application viscosity of paints on this basis can therefore be adjusted with deionized water alone, not requiring the additional use of organic solvents.

PROCESSING
Addition of driers

Water-emulsifiable driers such as Additol VXW 4940 N or cobalt free, Borchers Dry VP 0347 Aqua, have to be used for this purpose. Additions of 2 - 5 % of this substance (referred to the amount of solid binder) are recommended. In order to ensure homogeneous distribution in the paint, these driers should be diluted with deionized water at a ratio of 1 : 1 before being added. Optimum incorporation is to be expected when the drier is added to the material before grinding.

STORAGE

At temperatures up to 25 °C storage stability packed in original containers amounts to at least 365 days.

Synthetic resins containing water may freeze or get inhomogeneous at temperatures below 0 °C. By this the product will not suffer any damage, but the necessary regeneration requires extended heat treatment at 40 - 50 °C with continuous stirring. It is therefore recommended to ensure frostproof storage of such products.

Lowest storage temperature: - 2 °C

DISTINGUISHING FEATURES

Paints based on Resydrol AY 6173w/45WA have quick drying and similar salt spray resistance as solventborne alkyds.

4.0/17.07.2013 (replaces all previous versions)

• Worldwide Contact Info: www.allnex.com •

Disclaimer: Allnex Group companies ("Allnex") decline any liability with respect to the use made by anyone of the information contained herein. The information contained herein represents Allnex's best knowledge thereon without constituting any express or implied guarantee or warranty of any kind (including, but not limited to, regarding the accuracy, the completeness or relevance of the data set out herein). Nothing contained herein shall be construed as conferring any license or right under any patent or other intellectual property rights of Allnex or of any third party. The information relating to the products is given for information purposes only. No guarantee or warranty is provided that the product and/or information is adapted for any specific use, performance or result and that product and/or information do not infringe any Allnex and/or third party intellectual property rights. The user should perform its own tests to determine the suitability for a particular purpose. The final choice of use of a product and/or information as well as the investigation of any possible violation of intellectual property rights of Allnex and/or third parties remains the sole responsibility of the user.

© 2013 Allnex Belgium SA. All Rights Reserved

Notice: Trademarks indicated with the ®, ™ or * are registered, unregistered or pending trademarks of Allnex Belgium SA or its directly or indirectly affiliated Allnex Group companies.