

# RESYDROL<sup>®</sup> VAF 5540w/70MP

## TYPE

Non-drying alkyd resin, after neutralization with amines water-thinnable

## FORM OF DELIVERY (f.o.d.)

70 % in methoxypropanol (70MP)

## PRODUCT DATA

Determined per batch:

Dynamic Viscosity DIN EN ISO 3219 dynamic viscosity 54% BG (25 1/s; 23 °C)	[mPa.s]	300 - 550
---	---------	-----------

Acid Value DIN EN ISO 2114 acid value (solids)	[mg KOH/g]	42 - 53
--	------------	---------

Non-Volatile Matter DIN EN ISO 3251 non-volatile matter (1 h; 125 °C; 1 g)	[%]	68 - 72
--	-----	---------

Not continually determined:

Colour / Appearance VLN 250 colour appearance		pale yellow clear
---	--	----------------------

Density (Liquids) DIN EN ISO 2811-2 density approx. (20 °C)	[g/cm <sup>3</sup> ]	1,10
--	----------------------	------

Flash Point DIN EN ISO 1523 flash point approx.	[°C]	40
---	------	----

## SPECIAL PROPERTIES AND USE

Resydrol VAF 5540w/70MP is a non-drying alkyd resin for stoving applications providing

- good pigment wetting
- excellent mechanical properties
- very good storage stability.

In combination with waterdilutable melamine resins (preferably hexamethoxymethylmelamine grades like e.g. Cymel 303) Resydrol VAF 5540w is recommended as modifier resin for waterborne automotive OEM Primer Surfacer to improve leveling and appearance. According to our experience the blending ratio of 85 parts Resydrol VAF 5540w and 15 parts Cymel 303 (calculated on solid resin) is providing the most balanced properties of the final coating.

## DILUTABILITY

Resydrol VAF 5540w/70MP has to be neutralized with organic amines like e.g. Dimethyl ethanolamine, to gain waterdilutability. For 100 g of Resydrol VAF 5540w (as supplied) we recommend using 7 g of Dimethyl ethanolamine to achieve sufficient water dilutability and system stability.

Resydrol VAF 5540w is also soluble in water miscible solvents like glycol ethers and alcohols; nevertheless compatibility needs to be checked upfront.

## STORAGE

At temperatures up to 25 °C storage stability packed in original containers amounts to at least 365 days.

5.0/28.05.2014 ( replaces 4.0/17.07.2013 )

• Worldwide Contact Info: [www.allnex.com](http://www.allnex.com) •

Disclaimer: Allnex Group companies ("Allnex") decline any liability with respect to the use made by anyone of the information contained herein. The information contained herein represents Allnex's best knowledge thereon without constituting any express or implied guarantee or warranty of any kind (including, but not limited to, regarding the accuracy, the completeness or relevance of the data set out herein). Nothing contained herein shall be construed as conferring any license or right under any patent or other intellectual property rights of Allnex or of any third party. The information relating to the products is given for information purposes only. No guarantee or warranty is provided that the product and/or information is adapted for any specific use, performance or result and that product and/or information do not infringe any Allnex and/or third party intellectual property rights. The user should perform its own tests to determine the suitability for a particular purpose. The final choice of use of a product and/or information as well as the investigation of any possible violation of intellectual property rights of Allnex and/or third parties remains the sole responsibility of the user.

© 2013 Allnex Belgium SA. All Rights Reserved

Notice: Trademarks indicated with the ®, ™ or \* are registered, unregistered or pending trademarks of Allnex Belgium SA or its directly or indirectly affiliated Allnex Group companies.