

RESYDROL[®] VAF 6111w/60WA

TYPE

Oxidatively drying alkyd resin as aqueous emulsion, free of amines and ammonia

FORM OF DELIVERY (f.o.d.)

60 % in water (60WA), partially neutralized

Content of fatty acids

approx. 40 % special fatty acids (as triglycerides)

PRODUCT DATA

Determined per batch:

Dynamic Viscosity DIN EN ISO 3219 dynamic viscosity (10 1/s; 23 °C)	[mPa.s]	200 - 800
---	---------	-----------

pH-Value DIN ISO 976 pH-value (10 %)		5,5 - 9,0
--	--	-----------

Non-Volatile Matter DIN 55671 non-volatile matter (120 °C; 5 min)	[%]	58 - 62
---	-----	---------

Not continually determined:

Colour / Appearance VLN 250 colour		white
---------------------------------------	--	-------

Non-Volatile Matter DIN EN ISO 3251 non-volatile matter (1 h; 125 °C; 1 g)	[%]	58 - 62
--	-----	---------

Density (Liquids) DIN EN ISO 2811-2 density approx. (20 °C)	[g/cm ³]	1,07
--	----------------------	------

Flash Point (Pensky-Martens) DIN EN ISO 2719 flash point	[°C]	> 100
---	------	-------

SPECIAL PROPERTIES AND USE

Resydrol VAF 6111w comes without any organic solvents or amines. Stabilisation is reached by a special alkylphenoethoxylate-free carrier resin.

COMPATIBILITY

Resydrol VAF 6111w can be easily combined with other Resydrol binders, for example Resydrol AY 586w and Resydrol AY 430w, even for high gloss paints. Joint usage of Resydrol AY 548wtix gives thixotropic properties. Resydrol VAF 6111w can also be combined with acrylic emulsions, for example Mowilith[®] LDM 7451, however the compatibility should be tested carefully in advance.

APPLICATION

Resydrol VAF 6111w is not stable against high shear rates (3500 rpm) which are needed for the production of paints by pearl-mill for high gloss top coats. As dispersing additives we recommend Additol VXW 6208 or EFKA 4550.

Resydrol VAF 6111w is especially suitable for waterborne flat, semi gloss and high gloss paints for wood, walls and ceilings. Paints based on Resydrol VAF 6111w show low yellowing (also in the darkness) and a very good compromise between drying and open time.

Resydrol VAF 6111w can also be used for the production of solvent-free unpigmented and also pigmented wood stains, by using water dilutable Luconyl[®] (BASF), Disperfin[®] (Brockhues) or Napronyl[®] (Clariant) colour pastes. On special woods, for instance oak and tropical woods like mahagoni, the drying rate may be delayed and discolouring may occur.

For Resydrol VAF 6111w only water emulsifiable driers, preferably the alkylphenoethoxylate-free Additol VXW 6206, should be used. The usage of about 2 - 3 % drier, calculated on solid resin, is recommendable.

STORAGE

At temperatures up to 25 °C storage stability packed in original containers amounts to at least 180 days.

It is important to protect Resydrol VAF 6111w from frost; at low temperatures it has therefore to be stored under frostproof conditions.

Lowest storage temperature: - 2 °C

DISTINGUISHING FEATURES

Resydrol VAF 6111w is especially suitable for pigmented paints and as combination partner with other w/b binders. Resydrol VAF 6111w shows less yellowing and better drying than Resydrol VAS 6110w.

4.0/17.07.2013 (replaces all previous versions)

• Worldwide Contact Info: www.allnex.com •

Disclaimer: Allnex Group companies (*Allnex*) decline any liability with respect to the use made by anyone of the information contained herein. The information contained herein represents Allnex's best knowledge thereon without constituting any express or implied guarantee or warranty of any kind (including, but not limited to, regarding the accuracy, the completeness or relevance of the data set out herein). Nothing contained herein shall be construed as conferring any license or right under any patent or other intellectual property rights of Allnex or of any third party. The information relating to the products is given for information purposes only. No guarantee or warranty is provided that the product and/or information is adapted for any specific use, performance or result and that product and/or information do not infringe any Allnex and/or third party intellectual property rights. The user should perform its own tests to determine the suitability for a particular purpose. The final choice of use of a product and/or information as well as the investigation of any possible violation of intellectual property rights of Allnex and/or third parties remains the sole responsibility of the user.

© 2013 Allnex Belgium SA. All Rights Reserved

Notice: Trademarks indicated with the ®, ™ or * are registered, unregistered or pending trademarks of Allnex Belgium SA or its directly or indirectly affiliated Allnex Group companies.