

VIACRYL[®] SC 303/65XB

TYPE

Acrylic resin for cross-linking with amino resins

FORM OF DELIVERY (f.o.d.)

65 % in xylene / butanol (65XB)

SPECIAL PROPERTIES AND USE

 Automotive finishes, in particular for metallics, especially for metallic basecoats (wet-on-wet process).
 Stoving enamels with good outdoor stability and colour retention, for general industrial purposes.

PRODUCT DATA

Determined per batch:

 Dynamic Viscosity DIN EN ISO 3219
 dynamic viscosity [mPa.s] 19000 - 30000
 (25 1/s; 23 °C)

 Dynamic Viscosity DIN EN ISO 3219
 dynamic viscosity [mPa.s] 700 - 1300
 50% X
 (25 1/s; 23 °C)

 Colour Scale (Hazen) DIN EN ISO 6271-1
 Hazen colour value <= 80

 Acid Value DIN EN ISO 2114
 acid value [mg KOH/g] 10 - 15
 (solids)

 Non-Volatile Matter DIN EN ISO 3251
 non-volatile matter [%] 63 - 67
 (1 h; 125 °C; 2 g; EAC)

Not continually determined:

 Density (Liquids) DIN EN ISO 2811-2
 density [g/cm³] 1,01
 approx.
 (20 °C)

 Flash Point DIN EN ISO 1523
 flash point [°C] 27
 approx.

DILUTABILITY

xylene	}	methoxypropyl acetate	}
methyl ethyl ketone	}	ethanol	}
ethyl acetate	}	butanol	}
white spirit	»	butyl acetate	}
solvent naphtha 150/180	}	methoxypropanol	}
½ = substantial dilutability		» = very limited or no dilutability	
} = unlimited dilutability		¾ = limited dilutability	

COMPATIBILITY

% Viacryl SC 303	90	75	50	25	10
% other binder	10	25	50	75	90
Alkyd resins					
Vialkyd AC 371	»	»	»	»	»
Vialkyd AC 451	}	}	}	}	}
Vialkyd AR 400	»	»	»	»	»
Acrylic resins					
Viacryl SC 370	}	}	}	}	}
Amino resins					
Maprenal MF 590, MF 650	}	}	}	}	}
Maprenal MF 800, MF 900	}	}	}	}	}
Epoxy resins					
Beckopox EP 140	}	}	}	}	}
Beckopox EP 301	}	»	»	»	»
Duroxyn EF 900	»	»	»	»	»
Other binders					
epoxidized soya bean oil	}	}	»	»	»
benzyl butyl phthalate	}	}	}	}	}
CAB-381-0.5	}	}	}	}	}
} = definite compatibility					
» = very limited or no compatibility					

SUGGESTED USES

Viacryl SC 303/65XB is used in combination with melamine and urea resins for the formulation of stoving enamels. The principal application area is automotive finishes, in particular metallics and clear coats for two-coat metallic systems, in combination with cellulose acetobutyrate for basecoats in two-coat metallics, but also industrial applications such as electric night storage heaters, fluorescent lamps, household appliances, boilers and drying boxes.

In addition to their good adhesion, gloss, hardness, flexibility and corrosion resistance, paint films based on Viacryl SC 303 have very good stability to heat and to UV radiation. This is impressively evident in the case of top coats in two-coat metallic paints which, after prolonged outdoor exposure in Florida, show neither discolouration, cracking nor gloss impairment.

PROCESSING

As a thermosetting cross-linking acrylic resin Viacryl SC 303/65XB must be combined with amino resins. In the stoving temperature range of 120 - 150 °C, reactive melamine resins such as Maprenal MF 590 and Maprenal MF 650 are used as reaction partners.

In special cases it may be advantageous to combine the resin with the less reactive hexamethoxymethylmelamine resins, e. g. Maprenal MF 900. The most suitable combination ratios are 70 to 85 parts acrylic resin and 15 to 30 parts melamine resin, calculated on solids. With acid catalysts, such as maleic acid or p-toluene sulphonic acid, cross-linking takes place already at stoving temperatures as low as 90 °C. The addition of cellulose acetobutyrate speeds up physical drying.

Pigmentation

Viacryl SC 303 can be processed with usual pigments suitable for stoving enamels, and with aluminium pigments.

Depending on the shade required, the aluminium pigment content may be max. 4 % based on solid resin.

Dilution

The principal diluents used are aromatic hydrocarbons in combination with alcohols or glycol ethers or their esters.

STORAGE

At temperatures up to 25 °C storage stability packed in original containers amounts to at least 730 days.

DISTINGUISHING FEATURES

Compared to Viacryl SC 341 and Viacryl SC 370, Viacryl SC 303 is compatible with cellulose acetobutyrate, and therefore particularly suitable for the formulation of basecoats.

Producer:

CAB-381-0.5 (Eastman)

4.0/17.07.2013 (replaces all previous versions)

• Worldwide Contact Info: www.allnex.com •

Disclaimer: Allnex Group companies ("Allnex") decline any liability with respect to the use made by anyone of the information contained herein. The information contained herein represents Allnex's best knowledge thereon without constituting any express or implied guarantee or warranty of any kind (including, but not limited to, regarding the accuracy, the completeness or relevance of the data set out herein). Nothing contained herein shall be construed as conferring any license or right under any patent or other intellectual property rights of Allnex or of any third party. The information relating to the products is given for information purposes only. No guarantee or warranty is provided that the product and/or information is adapted for any specific use, performance or result and that product and/or information do not infringe any Allnex and/or third party intellectual property rights. The user should perform its own tests to determine the suitability for a particular purpose. The final choice of use of a product and/or information as well as the investigation of any possible violation of intellectual property rights of Allnex and/or third parties remains the sole responsibility of the user.

© 2013 Allnex Belgium SA. All Rights Reserved

Notice: Trademarks indicated with the ®, ™ or * are registered, unregistered or pending trademarks of Allnex Belgium SA or its directly or indirectly affiliated Allnex Group companies.