

# VIACRYL<sup>®</sup> SSC 6298w/67MP

## TYPE

Hydroxy functional copolymer

SPECIAL PRODUCT

## FORM OF DELIVERY (f.o.d.)

67 % in methoxypropanol (67MP)

## PRODUCT DATA

Determined per batch:

Dynamic Viscosity DIN EN ISO 3219  
dynamic viscosity [mPa.s] 40000 - 70000  
(10 1/s; 23 °C)

Acid Value DIN EN ISO 2114  
acid value [mg KOH/g] 36 - 40  
(solids)

Non-Volatile Matter DIN 55671  
non-volatile matter [%] 65 - 69  
(150 °C; 10 min)

Not continually determined:

Density (Liquids) DIN EN ISO 2811-2  
density [g/cm<sup>3</sup>] 1,04  
approx.  
(20 °C)

Flash Point DIN EN ISO 1523  
flash point [°C] 30  
approx.

## SPECIAL PROPERTIES AND USE

After neutralisation with amines water-dilutable binder for waterborne stoving enamels. Crosslinking with reactive water-dilutable melamine resins.

## STORAGE

At temperatures up to 25 °C storage stability packed in original containers amounts to at least 730 days.

3.0/17.07.2013 ( replaces all previous versions )

• Worldwide Contact Info: [www.allnex.com](http://www.allnex.com) •

Disclaimer: Allnex Group companies ("Allnex") decline any liability with respect to the use made by anyone of the information contained herein. The information contained herein represents Allnex's best knowledge thereon without constituting any express or implied guarantee or warranty of any kind (including, but not limited to, regarding the accuracy, the completeness or relevance of the data set out herein). Nothing contained herein shall be construed as conferring any license or right under any patent or other intellectual property rights of Allnex or of any third party. The information relating to the products is given for information purposes only. No guarantee or warranty is provided that the product and/or information is adapted for any specific use, performance or result and that product and/or information do not infringe any Allnex and/or third party intellectual property rights. The user should perform its own tests to determine the suitability for a particular purpose. The final choice of use of a product and/or information as well as the investigation of any possible violation of intellectual property rights of Allnex and/or third parties remains the sole responsibility of the user.

© 2013 Allnex Belgium SA. All Rights Reserved

Notice: Trademarks indicated with the ®, ™ or \* are registered, unregistered or pending trademarks of Allnex Belgium SA or its directly or indirectly affiliated Allnex Group companies.