

VIACRYL[®] VSC 6250w/65MP

TYPE

External cross-linking acrylate binder for application in cathodic electro dipping coating

FORM OF DELIVERY (f.o.d.)

65 % in methoxypropanol (65MP), non-neutralized

PRODUCT DATA

Determined per batch:

Dynamic Viscosity DIN EN ISO 3219 dynamic viscosity (25 1/s; 23 °C)	[mPa.s]	18000 - 35000
---	---------	---------------

Non-Volatile Matter DIN 55671 non-volatile matter (150 °C; 10 min)	[%]	63 - 67
--	-----	---------

Not continually determined:

Colour / Appearance VLN 250 colour appearance		yellow-orange cl-lightcloudy
---	--	---------------------------------

Non-Volatile Matter DIN EN ISO 3251 non-volatile matter (1 h; 125 °C; 1 g)	[%]	63 - 67
--	-----	---------

Density (Liquids) DIN EN ISO 2811-2 density approx. (20 °C)	[g/cm ³]	1,04
--	----------------------	------

Flash Point DIN EN ISO 1523 flash point approx.	[°C]	33
---	------	----

SPECIAL PROPERTIES AND USE

Viacryl VSC 6250w serves in combination with suitable curing agents (for example Additol VXW 6385) for the production of white or bright coloured electro dipping paints.

By means of suitable catalysis, for example with tin compounds, at baking temperatures of 160 °C, glossy and highly anticorrosive paint films can be manufactured.

Besides the conventional application as binder for pigmented primer or one-layer systems, Viacryl VSC 6250w may also be applied as clear paint for the production of transparent protective coatings on iron and non-iron metals due to its non-yellowing tendency.

STORAGE

At temperatures up to 25 °C storage stability packed in original containers amounts to at least 730 days.

5.0/17.07.2013 (replaces all previous versions)

• Worldwide Contact Info: www.allnex.com •

Disclaimer: Allnex Group companies ("Allnex") decline any liability with respect to the use made by anyone of the information contained herein. The information contained herein represents Allnex's best knowledge thereon without constituting any express or implied guarantee or warranty of any kind (including, but not limited to, regarding the accuracy, the completeness or relevance of the data set out herein). Nothing contained herein shall be construed as conferring any license or right under any patent or other intellectual property rights of Allnex or of any third party. The information relating to the products is given for information purposes only. No guarantee or warranty is provided that the product and/or information is adapted for any specific use, performance or result and that product and/or information do not infringe any Allnex and/or third party intellectual property rights. The user should perform its own tests to determine the suitability for a particular purpose. The final choice of use of a product and/or information as well as the investigation of any possible violation of intellectual property rights of Allnex and/or third parties remains the sole responsibility of the user.

© 2013 Allnex Belgium SA. All Rights Reserved

Notice: Trademarks indicated with the ®, ™ or * are registered, unregistered or pending trademarks of Allnex Belgium SA or its directly or indirectly affiliated Allnex Group companies.