

VIALKYD® AN 950/70X

TYPE

High-elastic thermosetting oil-free polyester resin

FORM OF DELIVERY (f.o.d.)

70 % in xylene (70X)

SPECIAL PROPERTIES AND USE

Outdoor durable, nonyellowing one coat stamping and deepdrawing coil-coating systems for aluminium, sheet steel and tin sheet as well as for automotive primer surfacers and metallic base coats.

PRODUCT DATA

Determined per batch:

Dynamic Viscosity DIN EN ISO 3219
dynamic viscosity [mPa.s] 2300 - 3100
(25 1/s; 23 °C)

Iodine Colour Number DIN 6162
iodine colour number <= 5

Non-Volatile Matter DIN 55671
non-volatile matter [%] 68 - 72
(120 °C; 5 min; 0,6 - 0,8 g)

Acid Value DIN EN ISO 2114
acid value [mg KOH/g] < 12
(solids)

Not continually determined:

Non-Volatile Matter DIN EN ISO 3251
non-volatile matter [%] 68 - 72
(1 h; 125 °C; 2 g)

Density (Liquids) DIN EN ISO 2811-2
density [g/cm³] 1,07
approx.
(20 °C)

Flash Point DIN EN ISO 1523
flash point [°C] 27
approx.

COMPATIBILITY

	90	75	50	25	10
% Vialkyd AN 950					
% other binder	10	25	50	75	90

Alkyd resins

Vialkyd AM 424 } } } } }

Silicone modified polyester resins

Vialkyd VTS 1202 } } } } }

Acrylic resins

Macrynal SM 510 } } } } }

Other binders

Beckopox EP 301 } } } } }

nitrocellulose 24 E } } } } }

} = definite compatibility

» = very limited or no compatibility

SUGGESTED USES

Spray coatings, stove cured

Vialkyd AN 950/70X is formulated with reactive melamine resins for coating systems for motor vehicles, household appliances, street signs, lighting fixtures as well as heaters or other components subjected to continuous heat load.

Vialkyd AN 950 can be crosslinked with melamine resin in ratios of 70 : 30 to 80 : 20 (alkyd resin : melamine resin). The curing schedule is 30 minutes at 120 - 140 °C.

Two-component systems

Vialkyd AN 950/70X (OH-value ca. 100 on solid resin) can be crosslinked with polyisocyanates such as Desmodur N (Bayer). Such systems can also be combined with hydroxy functional acrylic resins such as Macrynal SM 510.

Physical curing coating systems

In combination with thermoplastic film formers such as nitrocellulose and cellulose acetobutyrate it can be used for physical curing coating systems. Compatibility with the selected film former should first be investigated.

PROCESSING

Pigmentation

Vialkyd AN 950 has excellent pigment wetting properties with common used pigments for decorative systems so that it can be used as milling base for master batches.

Dilution

Aromatic hydrocarbons can be used for reduction when sufficient polar solvents such as ethoxypropyl acetate or methoxy propanol are also used.

Flow

When roller coated or sprayed the surface flow can be improved by adding 0.5 - 1 % Additol XL 122 or 0.3 - 5 % Additol XL 480 on total solid resin.

STORAGE

At temperatures up to 25 °C storage stability packed in original containers amounts to at least 730 days.

DISTINGUISHING FEATURES

For roller coated coil-coating systems Vialkyd AN 950/60SNBBG (in solvent naphtha 180/210 / butyl glycol) is recommended.

5.0/17.07.2013 (replaces all previous versions)

• Worldwide Contact Info: www.allnex.com •

Disclaimer: Allnex Group companies ("Allnex") decline any liability with respect to the use made by anyone of the information contained herein. The information contained herein represents Allnex's best knowledge thereon without constituting any express or implied guarantee or warranty of any kind (including, but not limited to, regarding the accuracy, the completeness or relevance of the data set out herein). Nothing contained herein shall be construed as conferring any license or right under any patent or other intellectual property rights of Allnex or of any third party. The information relating to the products is given for information purposes only. No guarantee or warranty is provided that the product and/or information is adapted for any specific use, performance or result and that product and/or information do not infringe any Allnex and/or third party intellectual property rights. The user should perform its own tests to determine the suitability for a particular purpose. The final choice of use of a product and/or information as well as the investigation of any possible violation of intellectual property rights of Allnex and/or third parties remains the sole responsibility of the user.

© 2013 Allnex Belgium SA. All Rights Reserved

Notice: Trademarks indicated with the ®, ™ or * are registered, unregistered or pending trademarks of Allnex Belgium SA or its directly or indirectly affiliated Allnex Group companies.