

VIALKYD[®] VAF 6091

TYPE

Long oil, air drying High Solids alkyd resin

FORM OF DELIVERY (f.o.d.)

100 %

RESIN COMPOSITION

(approx.)

89 % vegetable fatty acids (as triglycerides)

PRODUCT DATA

Determined per batch:

Dynamic Viscosity DIN EN ISO 3219

dynamic viscosity [mPa.s] 450 - 800
(25 1/s; 23 °C)

Iodine Colour Number DIN 6162

iodine colour number <= 6
50% WS

Acid Value DIN EN ISO 2114

acid value [mg KOH/g] < 10
(solids)

Non-Volatile Matter DIN 55671

non-volatile matter [%] 98 - 100
(120 °C; 5 min)

Not continually determined:

Non-Volatile Matter DIN EN ISO 3251

non-volatile matter [%] 98 - 100
(1 h; 125 °C; 1 g)

Density (Liquids) DIN EN ISO 2811-2

density [g/cm³] 0,95
approx.
(20 °C)

Flash Point (Pensky-Martens) DIN EN ISO 2719

flash point [°C] 130
approx.

SUGGESTED USES

Vialkyd VAF 6091 is a High Solids long oil alkyd resin for the production of High Solids primers, wood stains and top coats. A solid content of 90 % by weight is possible in white high gloss paints. Application properties are the same as with normal conventional alkyds. Applying paints based on Vialkyd VAF 6091 on primers usually need only one layer, which leads to additional reduction of solvent emission.

For environmental reasons we suggest the use of lead-free driers, for example zircone.

STORAGE

At temperatures up to 25 °C storage stability packed in original containers amounts to at least 730 days.

3.0/17.07.2013 (replaces all previous versions)

• Worldwide Contact Info: www.allnex.com •

Disclaimer: Allnex Group companies ("Allnex") decline any liability with respect to the use made by anyone of the information contained herein. The information contained herein represents Allnex's best knowledge thereon without constituting any express or implied guarantee or warranty of any kind (including, but not limited to, regarding the accuracy, the completeness or relevance of the data set out herein). Nothing contained herein shall be construed as conferring any license or right under any patent or other intellectual property rights of Allnex or of any third party. The information relating to the products is given for information purposes only. No guarantee or warranty is provided that the product and/or information is adapted for any specific use, performance or result and that product and/or information do not infringe any Allnex and/or third party intellectual property rights. The user should perform its own tests to determine the suitability for a particular purpose. The final choice of use of a product and/or information as well as the investigation of any possible violation of intellectual property rights of Allnex and/or third parties remains the sole responsibility of the user.
© 2013 Allnex Belgium SA. All Rights Reserved

Notice: Trademarks indicated with the ®, ™ or * are registered, unregistered or pending trademarks of Allnex Belgium SA or its directly or indirectly affiliated Allnex Group companies.