



Product Information

Aquarez PVB 519 (formerly DP415-199)

Provisional Product Description

Aquarez PVB 519 is a water-based dispersion of a Polyvinyl Butyral plasticised with castor oil, suitable for use in coating and adhesive applications. Based on higher molecular weight polymer it produces a film with superior tensile strength, water resistance and forms transparent films when dried at room temperature. It has excellent coating properties on many substrates, including glass, wood, plastics and metals. It is suitable for use in Protective Coatings, Strippable Coatings and as a Textile Binder.

Product Features

- Zero VOC content
- Film forms at ambient temperature
- Free of APEO surfactants
- Excellent water resistance
- Resistant to heat and UV
- PVB: Plasticiser ratio 7:3
- Good storage stability & low sedimentation.
- Good compatibility with other Waterbased polymer dispersions

Typical Properties (provisional)

- Total solid content 47.0%
- Active solid content 44.5%
- Viscosity <1000 mPA.s
- pH 9-10
- Particle Size <4µm

Application & Dosage

This product can be used as-supplied, or can be further formulated with compatible waterborne resin dispersions, thickeners, pigments and cross-linkers in coatings, adhesives and sealants. Its excellent tensile strength and cohesive properties make it ideally suited for the formulation of temporary protective coatings for metals, glass, composites and plastics.

Packaging and Storage

Aquarez PVB 519 can be supplied in 200Kg HDPE Drum and 1000Kg Intermediate Bulk Container. The product should be stored in dry, cool location away from heat or direct sunlight ideally between 5°C and 30°C and it must be protected from freezing. If stored for long periods periodic, slow speed mechanical agitation is recommended prior to using product to ensure homogeneity.

Revision 3, April 16

The recommendations made above are general in nature...Although every effort has been made to supply reliable data, it is for informational purposes only. We cannot guarantee the results as stated to be obtained since we have no control over the end use of the material. Each user must make their own tests to determine the suitability of the material for their own use. Nothing contained herein is intended as a recommendation to use our products to infringe any patent.

The recommendations made above are general in nature...Although every effort has been made to supply reliable data, it is for informational purposes only. We cannot guarantee the results as stated to be obtained since we have no control over the end use of the material. Each user must make their own tests to determine the suitability of the material for their own use. Nothing contained herein is intended as a recommendation to use our products to infringe any patent.