

Baxxodur[®] EC 310

Amine curing agent for the epoxy industry

July 2018 | [Data Sheet](#) | Replaced Version October 2013

TI-CI 0019 / Page 1 of 2

® = registered trademark of BASF SE

System description

Baxxodur EC 310 is a polyether amine based curing agent with low viscosity and a long pot life.

Features

- Excellent adhesion
- Good flexibility
- Good toughness
- Good thermal shock resistance
- Low color

Applications

- Structural adhesive
- Composite
- Construction
- Coating

Characteristics (typical values)

Curing agent

Chemical properties	Value	Unit	Method
Color	max. 50	APHA	DIN EN 1557
Refractive Index at 20 °C	1.4604	-	DIN 51423
Density at 20 °C	0.987	[g/cm ³]	DIN 2811-3
Amine Value	~ 350	[mg KOH/g]	DIN 16945
Viscosity at 20 °C	~ 102	[mPa*s]	DIN 3219

Mixing
(parts by weight)

Component	Parts by weight
Standard Epoxy Resin based on Bisphenol-A (EEW = 185 g/Eq)	100
Baxxodur® EC 310 (AHEW = 81 g/Eq)	43

Processing
(typical values)

Mixing Properties	Value	Unit	Test method
Viscosity of mixture at 23°C	1710	[mPa*s]	DIN EN ISO 3219
Open time at 23°C ¹	150	[min]	DIN 16945 ²
Time to reach 6 Pa*s at 23°C	224	[min]	DIN 16945 ²
Time to reach 6 Pa*s at 45°C	135	[min]	DIN 16945 ²
Time to reach 6 Pa*s at 75°C	32	[min]	DIN 16945 ²
Gel point at 70°C	69	[min]	ASTM D4473 ³
Gel point at 90°C	23	[min]	ASTM D4473 ³
Gel point at 110°C	10	[min]	ASTM D4473 ³

¹ Time to double the initial mix viscosity
² Anton Paar rheometer; plate-plate diameter: 25 mm; gap: 1mm; shear rate of 100 1/s
³ Anton Paar rheometer; plate-plate diameter: 25 mm; gap: 1 mm; oscillation

Cured Resin
(typical values)

Epoxy resin cured with Baxxodur EC 310 for 2h at 80 °C, 2h 100 °C, 2h 120 °C, 2h 140 °C, 2h 160 °C

Mechanical Properties	Value	Unit	Test method
Tg	89	[°C]	DSC, mod., 5 K/min
HDT	85	[°C]	DIN EN ISO 75-2
Tensile strength	64	[MPa]	DIN EN ISO 527-2
Tensile modulus	2800	[MPa]	DIN EN ISO 527-2
Tensile elongation at F _{max}	5.2	[%]	DIN EN ISO 527-2
Flexural strength	107	[MPa]	DIN EN ISO 178
Flexural modulus	2932	[MPa]	DIN EN ISO 178
Charpy (impact strength)	59	[kJ/m ²]	DIN EN ISO 179-1

Additional technical data for this product is available upon request.

Contact

E-Mail: info.intermediates@basf.com

Internet: www.intermediates.basf.com

Note

The data contained in this publication is based on our current knowledge and experience. In view of the many factors that may affect processing and application of our product, the data does not relieve processors from carrying out their own investigations and tests; neither does the data imply any guarantee of certain properties, nor the suitability of the product for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein may change without prior information and do not constitute the agreed contractual quality of the product. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed. The safety data given in this publication is for information purposes only and does not constitute a legally binding Material Safety Data Sheet (MSDS). The relevant MSDS can be obtained upon request from your supplier or you may contact BASF directly at www.intermediates.basf.com.