

## Witcobond<sup>®</sup> 386-51D

## Technical Data

Witcobond 386-51D is an aqueous polyurethane dispersion with no free isocyanate.

### Typical Dispersion Properties

Solids Content (%)	59 - 61
pH at 25°C	7 - 9
Viscosity at 25°C (cps)	50 - 400
Appearance	White
Polyurethane Dispersion Type	Aliphatic, polyether, anionic
Co-solvent: % / Type	0
Specific Gravity at 25°C	1.06
T <sub>g</sub> / Minimum Film-Forming Temperature (°C)	- / 0

### Typical Film Properties

Tensile strength (psi) / (MPa)	6000 / 40
100 % Modulus (psi) / (MPa)	300 / 2
Ultimate Elongation (%)	1000
Blocking Temperature(°C)	170
Hardness: König / Sward / Pencil	15 / - / -

### Safety, Storage and Handling Information

The appropriate Material Safety Data Sheet must be consulted before Witcobond 386-51D is stored, transported or used. Witcobond 386-51D dispersion should be protected from frost, and stored between 5°C and 30°C. Witcobond polyurethane dispersions should be stirred thoroughly before use. Under these storage conditions Witcobond 386-51D in original, unopened containers has a shelf life of 12 months.



Chemtura  
199 Benson Road  
Middlebury, CT 06749, USA

APAC: +86 21 386 665 26  
EU: +44 1905 794 795  
Korea: +82 2 5413806

NA: +1 877 873 0273  
Central America: +52 55 5010 6607  
Latin America: +55 19 3522 5082



Baxenden Chemicals Limited  
Union Lane,  
Droitwich, WR9 9BB, UK

Witcobond 386-51D is manufactured and distributed by Chemtura Corporation and its subsidiary company, Baxenden Chemicals

Limited

The information contained herein relates to a specific Chemtura product and its use, and is based on information available as of the date hereof. Additional information relating to the product can be obtained from the pertinent Material Safety Data Sheets. Nothing in this Technical Data Sheet shall be construed to modify any of Chemtura's standard terms and conditions of sale under which the product is sold by Chemtura. NOTHING IN THIS TECHNICAL DATA SHEET SHALL BE CONSTRUED TO CONSTITUTE A REPRESENTATION OR WARRANTY, EXPRESS OR IMPLIED, REGARDING THE PRODUCT'S CHARACTERISTICS, USE, QUALITY, SAFETY, MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein shall constitute permission or recommendation to practice any intellectual property without the permission of the owner.

Chemtura and the Chemtura logo are trademarks of Chemtura Corporation or one of its subsidiaries.

Copyright © 2011 Chemtura Corporation. All rights reserved.

*Witcobond 386-51D is manufactured and distributed by Chemtura Corporation and its subsidiary company, Baxenden Chemicals*

*Limited*

The information contained herein relates to a specific Chemtura product and its use, and is based on information available as of the date hereof. Additional information relating to the product can be obtained from the pertinent Material Safety Data Sheets. Nothing in this Technical Data Sheet shall be construed to modify any of Chemtura's standard terms and conditions of sale under which the product is sold by Chemtura. NOTHING IN THIS TECHNICAL DATA SHEET SHALL BE CONSTRUED TO CONSTITUTE A REPRESENTATION OR WARRANTY, EXPRESS OR IMPLIED, REGARDING THE PRODUCT'S CHARACTERISTICS, USE, QUALITY, SAFETY, MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein shall constitute permission or recommendation to practice any intellectual property without the permission of the owner.

Chemtura and the Chemtura logo are trademarks of Chemtura Corporation or one of its subsidiaries.

Copyright © 2011 Chemtura Corporation. All rights reserved.