



## Data Sheet

Pub. No. 2008161A

# Butvar® B-90

Butvar B-90 is a thermoplastic, polyvinyl butyral resin which offers a unique combination of properties for coating or adhesive applications. The use or addition of polyvinyl butyral to a system imparts adhesion, toughness, and flexibility. PVB retains the clarity of the coating and offers reactive hydroxyl sites for crosslinking with thermoset. Butvar B-90 is formulated into many applications including:

- ☒ WASH PRIMERS AND GENERAL METAL OR WOOD COATINGS
- ☒ BINDERS FOR ADHESIVES AND STRUCTURAL COMPOSITES
- ☒ BINDERS FOR INKS AND TONERS

## Physical Properties

### Specifications

Property	Limits	Test Method
Hydroxyl Content, % (Expressed as % Polyvinyl Alcohol)	18.5-20.5	Titration WS-03-90-09B
Solution Viscosity, cps (6% solids in methanol @ 20°C)	13.0-17.0	Ostwald Viscometer WS-03-90-01C
Volatile Content, %	5.0 max.	Thermogravimetric WS-03-90-03B

### Useful Information

Form	White, free-flowing powder
Acetate Content, (% Polyvinyl Acetate)	2.5 maximum
Butyral Content, (% Polyvinyl Butyral)	80 (approximate)
Molecular Weight* (Mw)	70,000-100,000
Specific Gravity	1.100
Glass Transition Temperature (T <sub>g</sub> ), °C	72-78
* Size exclusion chromatography with low angle laser light scattering standard	



---

For Technical Service assistance, call 413- 730-3241 or FAX 413-730-3394.  
For Customer Order assistance, call toll-free 1-800-964-5224 or FAX 314-674-5147.  
Additional information follows.

---

**NOTICE:** While the information contained herein is presented in good faith and believed to be correct as of the date hereof, Solutia Inc. does not guarantee satisfactory results from reliance upon such information, disclaims all liability for any loss or damage arising out of any use of this information or the products to which said information refers and **MAKES NO EXPRESS OR IMPLIED REPRESENTATION OR WARRANTY AS TO THE FITNESS, MERCHANTABILITY OR ANY OTHER MATTER WITH RESPECT TO THE INFORMATION OR PRODUCTS**, except as set forth in Solutia's standard conditions of sale. Nothing contained herein is to be construed as a recommendation to use any product or process in conflict with any patent, and Solutia Inc. makes no representation or warranty, express or implied, that the use thereof will not infringe any patent.

®Registered Trademark of Solutia Inc.