

Technical Data Sheet

EPIKURE™ Curing Agent 3273

Product Description

EPIKURE™ Curing Agent 3273 is a modified aliphatic amine supplied at 100 percent solids. It is designed for use with epoxy polyacrylate resins in formulating high solids, high build coatings. Additionally, EPIKURE Curing Agent 3273 is well-suited for fast setting, equal volume adhesives.

Application Areas/Suggested Uses

- Rapid setting adhesives
- Tooling gel coats
- Small casting applications
- Equal volume packaged adhesives

Benefits

- Rapid cure rates in thin sections
- Low temperature cure
- Convenient combining ratio

Sales Specifications

Property	Value	Unit	Test Method
Amine as KOH	420 - 480	mg/g	ASTM D2896
Color	6 max.	Gardner	ASTM D1544
Viscosity at 25°C	1200 - 2000	cP	ASTM D2196

Typical Properties

Property	Value	Unit	Test Method
Equivalent Weight Approx.	90		
Flash Point	>200	°F	Setaflash
Pounds/Gallon @ 25°C	8.18	lbs/gal	ASTM D1475

EPIKURE Curing Agent 3273
<https://www.hexion.com/en-US/product/epikure-curing-agent-3273>

Generated: May 22, 2019
 Issue Date:
 Revision: 8/1/2001 12:00:00 AM

® and ™ Licensed trademarks of Hexion Inc.

The information provided herein was believed by Hexion Inc. ("Hexion") to be accurate at the time of preparation or prepared from sources believed to be reliable, but it is the responsibility of the user to investigate and understand other pertinent sources of information, to comply with all laws and procedures applicable to the safe handling and use of the product and to determine the suitability of the product for its intended use. All products supplied by Hexion are subject to Hexion's terms and conditions of sale. **HEXION MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE OR CONCERNING THE ACCURACY OF ANY INFORMATION PROVIDED BY HEXION**, except that the product shall conform to Hexion's specifications. Nothing contained herein constitutes an offer for the sale of any product.

General Information

EPIKURE Curing Agent 3273 demonstrates a versatile combining ratio when formulated with modified epoxy resins (EPON™ Resins 8111 and 8121). This makes it well-suited for applications where rapid curing 1:1 by volume systems are desired. The formulating latitude inherent in EPIKURE Curing Agent 3273 yields a useful combining ratio in the range of 60 to 100 parts resin when used with a modified liquid epoxy such as EPON Resin 8121.

Safety, Storage & Handling

Please refer to the MSDS for the most current Safety and Handling information.

Please refer to the Hexion web site for Shelf Life and recommended Storage information.

To preserve product quality and prevent discoloration, it is recommended that a nitrogen blanket be maintained on the headspace of an opened container and that storage / handling temperatures in excess of 50°C (122°F) be avoided. Spillage around the opening of the container from dispensing operations will form a crystalline residue. This residue is not soluble in the curing agent nor the resin, and certain measures should be taken to prevent it from contaminating the remaining contents of the container. The crystalline residue should be removed with a warm damp wash cloth PRIOR to re-opening the container for dispensing.

EPIKURE Curing Agent 3273 should be stored in tightly sealed containers in a dry location at normal room temperature. Exposure to moisture causes an increase in viscosity and reactivity, the degree of increase depending upon the amount of moisture which has been absorbed. This material may darken with age without degradation of properties.

Exposure to these materials should be minimized and avoided, if feasible, through the observance of proper precautions, use of appropriate engineering controls and proper personal protective clothing and equipment, and adherence to proper handling procedures. None of these materials should be used, stored, or transported until the handling precautions and recommendations as stated in the Material Safety Data Sheet (MSDS) for these and all other products being used are understood by all persons who will work with them. Questions and requests for information on Hexion Inc. ("Hexion") products should be directed to your Hexion sales representative, or the nearest Hexion sales office. Information and MSDSs on non-Hexion products should be obtained from the respective manufacturer.

Packaging

Available in bulk and drum quantities.

Contact Information

For product prices, availability, or order placement, please contact customer service:

www.hexion.com/Contacts/

For literature and technical assistance, visit our website at: www.hexion.com