

Technical Data Sheet

EPIKURE™ Curing Agent 3381

Product Description

EPIKURE™ Curing Agent 3381 is a very low viscosity, modified cycloaliphatic amine, light colored epoxy curing agent. Systems formulated with EPIKURE Curing Agent 3381 exhibit good chemical resistance and color stability. It is ideally suited for civil engineering sealers and architectural coatings.

Application Areas/Suggested Uses

- Civil engineering sealers
- Decoupage coatings
- Grouts
- Mortars
- Architectural pastel, high-build coatings

Benefits

- Low mixed viscosity
- Good flexibility
- Excellent gloss and color stability
- Good chemical resistance
- Positive cure under damp cool conditions

Sales Specifications

Property	Value	Unit	Test Method
Amine Value	290 - 360	mg/g	ASTM D2896
Color	1	Gardner	ASTM D1544
Viscosity	50 - 100	cP	ASTM D2196

Typical Properties

EPIKURE Curing Agent 3381
<https://www.hexion.com/en-US/product/epikure-curing-agent-3381>

Generated: May 22, 2019
 Issue Date:
 Revision: 8/1/2007 12:00:00 AM

® and ™ Licensed trademarks of Hexion Inc.

The information provided herein was believed by Hexion Inc. ("Hexion") to be accurate at the time of preparation or prepared from sources believed to be reliable, but it is the responsibility of the user to investigate and understand other pertinent sources of information, to comply with all laws and procedures applicable to the safe handling and use of the product and to determine the suitability of the product for its intended use. All products supplied by Hexion are subject to Hexion's terms and conditions of sale. **HEXION MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE OR CONCERNING THE ACCURACY OF ANY INFORMATION PROVIDED BY HEXION**, except that the product shall conform to Hexion's specifications. Nothing contained herein constitutes an offer for the sale of any product.

Property	Value	Unit	Test Method
Appearance	Clear and free of foreign particles	Mix ratio	
Density @ 25°C	8.3	lbs/gal	ASTM D1475
EEW 190 Epoxy	50 - 65	phr	
Equivalent Weight Approx.	95		
Flash Point	>100	°C	ASTM D3278
Mix Ratio	0		

Safety, Storage & Handling

Please refer to the MSDS for the most current Safety and Handling information.

Please refer to the Hexion web site for Shelf Life and recommended Storage information.

Exposure to these materials should be minimized and avoided, if feasible, through the observance of proper precautions, use of appropriate engineering controls and proper personal protective clothing and equipment, and adherence to proper handling procedures. None of these materials should be used, stored, or transported until the handling precautions and recommendations as stated in the Material Safety Data Sheet (MSDS) for these and all other products being used are understood by all persons who will work with them. Questions and requests for information on Hexion Inc. ("Hexion") products should be directed to your Hexion sales representative, or the nearest Hexion sales office. Information and MSDSs on non-Hexion products should be obtained from the respective manufacturer.

Packaging

Available in bulk and drum quantities.

Contact Information

For product prices, availability, or order placement, please contact customer service:

www.hexion.com/Contacts/

For literature and technical assistance, visit our website at: www.hexion.com