

Technical Data Sheet

HELOXY™ Modifier 61

Product Description

HELOXY™ Modifier 61 is a commercial grade butyl glycidyl ether. A low viscosity, virtually colorless monoepoxide, it is widely used in the viscosity reducing modification of epoxy resin formulations.

Benefits

- Most efficient epoxy resin viscosity reduction of all common epoxy functional modifiers
- Outstanding substrate and filler wetting characteristics
- Excellent retention of physical strength and thermal properties of base formulations

Sales Specifications

Property	Value	Unit	Test Method
Color	1	Gardner	ASTM D1544
Viscosity at 25°C	1 - 2	cP	ASTM D445
Weight per Epoxide	140 - 155	g/eq	ASTM D1652

Typical Properties

Property	Value	Unit
Density	7.6 - 7.8	lbs/gal

General Information

The relatively low molecular weight of HELOXY 61 makes it the most efficient common monoepoxide in reducing the viscosity of basic epoxy resin formulations. A comparison of this property to that of other representative Heloxy modifiers is illustrated in Figure 1.

As with any monoepoxide, modification of basic epoxy resins with HELOXY 61 reduces the average functionality of the mixture thereby lowering overall cured state performance. However, due to its excellent viscosity reduction characteristics, relatively low levels of HELOXY 61 are normally needed to attain desired viscosity reductions and these compromises in performance properties are held to a minimum. In any application, the amount of HELOXY 61 used in the formulation should be limited to that necessary to yield the required viscosity reduction. The maximum recommended quantity of HELOXY 61 is about 20 percent by weight of the resin portion.

HELOXY 61 is compatible with other epoxy resins in all proportions and is easily blended with liquid resins at room temperature. If preferred, a pre-blend of HELOXY 61 and a standard bisphenol A based liquid epoxy resin at a viscosity selected for easy handling is available as EPON™ Resin 815C. For information on properties and suggested uses of this resin, please consult the appropriate product literature.

HELOXY Modifier 61

<http://hexioninternet.azurewebsites.net/en-US/product/heloxymodifier-61>

Generated: April 25, 2019

Issue Date:

Revision: 7/1/2016 12:00:00 AM

© and ™ Licensed trademarks of Hexion Inc.

The information provided herein was believed by Hexion Inc. ("Hexion") to be accurate at the time of preparation or prepared from sources believed to be reliable, but it is the responsibility of the user to investigate and understand other pertinent sources of information, to comply with all laws and procedures applicable to the safe handling and use of the product and to determine the suitability of the product for its intended use. All products supplied by Hexion are subject to Hexion's terms and conditions of sale. **HEXION MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE OR CONCERNING THE ACCURACY OF ANY INFORMATION PROVIDED BY HEXION**, except that the product shall conform to Hexion's specifications. Nothing contained herein constitutes an offer for the sale of any product.

Curing agents that are recommended for unmodified basic liquid epoxy resins can also be used with compositions containing HELOXY 61. When calculating the proper stoichiometric amount of curing agent to be used with HELOXY 61 modified resins, differences in epoxy content of the resin resulting from this modification are small and can generally be ignored at modification levels below 10 parts per hundred resin (phr).

Unless excessive amounts of HELOXY 61 are used, the physical properties of the cured systems are not seriously affected at room temperature. However, physical and electrical properties at elevated temperatures may be reduced considerably. Data listed in Table 1 illustrate the effect of HELOXY 61 on systems cured with various curing agents including conventional polyamines, anhydrides, and EPIKURE™ 3072 Curing Agent.

Figure 1 / Viscosity reduction with HELOXY Modifiers



Safety, Storage & Handling

Please refer to the MSDS for the most current Safety and Handling information.

Please refer to the Hexion web site for Shelf Life and recommended Storage information.

Exposure to these materials should be minimized and avoided, if feasible, through the observance of proper precautions, use of appropriate engineering controls and proper personal protective clothing and equipment, and adherence to proper handling procedures. None of these materials should be used, stored, or transported until the handling precautions and recommendations as stated in the Material Safety Data Sheet (MSDS) for these and all other products being used are understood by all persons who will work with them. Questions and requests for information on Hexion Inc. ("Hexion") products should be directed to your Hexion sales representative, or the nearest Hexion sales office. Information and MSDSs on non-Hexion products should be obtained from the respective manufacturer.

Packaging

Available in bulk and drum quantities.

Contact Information

For product prices, availability, or order placement, please contact customer service:

www.hexion.com/Contacts/

For literature and technical assistance, visit our website at: www.hexion.com

HELOXY Modifier 61

<http://hexioninternet.azurewebsites.net/en-US/product/helox-modifier-61>

Generated: April 25, 2019

Issue Date:

Revision: 7/1/2016 12:00:00 AM

® and ™ Licensed trademarks of Hexion Inc.

The information provided herein was believed by Hexion Inc. ("Hexion") to be accurate at the time of preparation or prepared from sources believed to be reliable, but it is the responsibility of the user to investigate and understand other pertinent sources of information, to comply with all laws and procedures applicable to the safe handling and use of the product and to determine the suitability of the product for its intended use. All products supplied by Hexion are subject to Hexion's terms and conditions of sale. **HEXION MAKES NO WARRANTY, EXPRESS OR IMPLIED, CONCERNING THE PRODUCT OR THE MERCHANTABILITY OR FITNESS THEREOF FOR ANY PURPOSE OR CONCERNING THE ACCURACY OF ANY INFORMATION PROVIDED BY HEXION**, except that the product shall conform to Hexion's specifications. Nothing contained herein constitutes an offer for the sale of any product.