



TECHNICAL DATA SHEET

G-Cure® 107A70 An acrylic polyol (17-0107)

General description:

G-Cure 107A70 acrylic resin is a hydroxyl functional acrylic copolymer designed to produce low VOC high performance coatings. Coatings with an application VOC of 3.0 lbs/gal can be produced. It will react at room temperature with aliphatic polyisocyanates to give excellent application properties. Coatings formulated with G-Cure 107A70 exhibit excellent chemical and weathering resistance with very good gloss retention.

Technical features:

1. 3.0 lbs/gal VOC coatings
2. Excellent chemical and weathering resistance
3. Good gloss retention

Suggested uses:

1. Heavy-duty industrial maintenance
2. Railcar, bridge and heavy equipment coatings

Delivery form: 70.0% non-volatile in Methyl n-Amyl Ketone

Typical properties:

Property	Value	Units	Method *
Non-volatile, by weight	70.0 ± 1.5	%	1 – 1
Viscosity, Brookfield (77°F)	1500 – 2500	cps	2 – 2
Hydroxyl value (on n.v.)	114 – 129		6 – 1
Color	100 maximum	APHA	3 – 2
Appearance	clean, clear and free from extraneous matter; may turn opaque when stored below 30°F: if this occurs, warm above 40°F until clear		7 – 1

*SDM: Nuplex Resins methods of determination (available on request)

HEW on n.v.: 460
Density: 8.50 ± 0.10lbs./gal. Non-volatiles, by vol.: 63.0%
Flash point: 101 °F Setaflash

On DSL Inventory

Recommended Reaction Ratios: 655 gm G-Cure 107A70/ 191 gm Tolonate HDT (Rhodia)
655 gm G-Cure 107A70/ 194 gm Desmodur N-3300 (Bayer)

Updated: June, 2008

All information, recommendations and suggestions, concerning the product and its use, are believed to be reliable. However, Nuplex Resins gives no assurance as to the accuracy, completeness, or adequacy for a particular purpose. It is the user's responsibility to determine the suitability for its own use of the products. No guarantee (whether expressed or implied) is made by Nuplex Resins as to the results to be obtained from using the described products, nor shall Nuplex Resins be liable for any use by others of the described products. Users are responsible for ensuring compliance with local legislation and obtaining the necessary certifications and authorizations. All orders are subject to the general conditions of sale of Nuplex Resins, which are printed overleaf and/or can be downloaded from www.nuplexresins.com. All of user's general terms and conditions are herewith deemed rejected. Nuplex Resins owns all copyrights and other intellectual property rights in the contents of this document. Reproduction or redistribution in any form is not allowed.