



## TECHNICAL DATA SHEET

### G-Cure® 867PWF60

An acrylic polyol (17-0867)

#### General description:

G-Cure 867PWF60 acrylic resin is a hydroxyl functional acrylic copolymer designed to react at room temperature with aliphatic polyisocyanates to produce high performance coatings. Coatings formulated with G-Cure 867PWF60 exhibit outstanding durability, chemical resistance and color retention. Coatings produced with G-Cure 867PWF60 are suitable for metal, wood and plastic, or heat sensitive substrates.

#### Technical features:

1. Excellent chemical resistance and color retention
2. Outstanding durable
3. Suitable for various substrates

#### Suggested uses:

1. Transportation and recreational finishes
2. Industrial maintenance coatings

**Delivery form:** 60.0% non-volatile in PM acetate/ ethylbenzene/ solvent 90 (55/ 25/ 20 pbw)

#### Typical properties:

Property	Value	Units	Method *
Non-volatile, by weight	60.0 ± 2.0	%	1 – 1
Viscosity, Brookfield (77°F)	3500 – 5000	cps	2 – 2
Hydroxyl value (on n.v.)	80 – 95		6 – 1
Color	100 maximum	APHA	3 – 2
Appearance	clean, clear and free from extraneous matter; may turn opaque when stored below 30°F: if this occurs, warm above 40°F until clear		7 – 1

\*SDM: Nuplex Resins methods of determination (available on request)

HEW on n.v.: 635  
Density: 8.50 ± 0.10lbs./gal. Non-volatiles, by vol.: 55.0%  
Flash point: 59°F Setaflash

*On DSL Inventory*

**Recommended Reaction Ratios:** 1058 gm G-Cure 867PWF60/ 255 gm Tolonate 75BX(Rhodia)  
1058 gm G-Cure 867PWF60/ 255 gm Desmodur N-75 (Bayer)

**Updated:** June, 2008

All information, recommendations and suggestions, concerning the product and its use, are believed to be reliable. However, Nuplex Resins gives no assurance as to the accuracy, completeness, or adequacy for a particular purpose. It is the user's responsibility to determine the suitability for its own use of the products. No guarantee (whether expressed or implied) is made by Nuplex Resins as to the results to be obtained from using the described products, nor shall Nuplex Resins be liable for any use by others of the described products. Users are responsible for ensuring compliance with local legislation and obtaining the necessary certifications and authorizations. All orders are subject to the general conditions of sale of Nuplex Resins, which are printed overleaf and/or can be downloaded from [www.nuplexresins.com](http://www.nuplexresins.com). All of user's general terms and conditions are herewith deemed rejected. Nuplex Resins owns all copyrights and other intellectual property rights in the contents of this document. Reproduction or redistribution in any form is not allowed.