



TECHNICAL DATA SHEET

Setal 10-1346

A chlorinated polyolefin resin solution

Status: Proprietary
Customer: Akzo Nobel BU Transportation
Akzo Nobel Code: 1X251
Description: Chlorinated polyolefin resin solution
Delivery form: 1% non-volatile in xylene / VM&P/ n-butyl acetate
Ratio of solvents: 70 / 20 / 10 pbw

Typical properties:

Property	Value	Units	Method *
Non-volatile, by weight	1.0 ± 0.10	%	1 – 1
Viscosity, as supplied	< A1	Gardner-Holdt	2 – 1
Color	8 maximum	Gardner	3 – 1
Appearance	Clean, clear and free from extraneous matter		7 – 1

* SDM: Nuplex Resins methods of determination (available on request)

Density: 7.00 ± 0.10 lbs./gal
Flash point: 15°F Setaflash
Non-volatile, by vol 1.2% *On DSL Inventory*

Updated: January, 2009

All information, recommendations and suggestions, concerning the product and its use, are believed to be reliable. However, Nuplex Resins gives no assurance as to the accuracy, completeness, or adequacy for a particular purpose. It is the user's responsibility to determine the suitability for its own use of the products. No guarantee (whether expressed or implied) is made by Nuplex Resins as to the results to be obtained from using the described products, nor shall Nuplex Resins be liable for any use by others of the described products. Users are responsible for ensuring compliance with local legislation and obtaining the necessary certifications and authorizations. All orders are subject to the general conditions of sale of Nuplex Resins, which are printed overleaf and/or can be downloaded from www.nuplexresins.com. All of user's general terms and conditions are herewith deemed rejected. Nuplex Resins owns all copyrights and other intellectual property rights in the contents of this document. Reproduction or redistribution in any form is not allowed.