



TECHNICAL DATA SHEET

Setal 11-3466

Pure long oil soybean alkyd resin

General description:

Setal 11-3466 is a pure long oil soybean alkyd supplied at 70% n.v. in mineral spirits. Coatings based upon Setal 11-3466 have exceptionally high specular gloss and gloss retention. These coatings have good color retention and exterior durability. Setal 11-3466 meets the performance and compositional requirements of Federal Specification TT-R-266, Type I, Class A.

Technical features:

1. Resin provides exterior durability and gloss retention
2. Provides good color retention and resistance to the elements
3. Provides good flow, leveling and flexibility in enamels

Suggested uses:

1. Marine, deck, porch and trim enamels
2. Industrial maintenance primers and shop coats
3. Bridge paints and architectural coatings

Delivery form: 70% non-volatile in mineral spirits / xylene (97 / 3 pbw)

Typical properties:

Property	Value	Units	Method *
Non-volatiles, by weight	70.0 ± 1.0	%	1 – 1
Viscosity	Z – Z2	Gardner-Holdt	2 – 1
Acid value, on solids	10 maximum		5 – 1
Color	6 maximum	Gardner	3 – 1
Appearance	clean, clear and free from extraneous matter		7 – 1

* SDM: Nuplex Resins methods of determination (available on request)

Density: 7.95 ± 0.10 lbs./gal HEW on n.v. = 1700
Reduced viscosity: B – D @ 50% n.v. in mineral spirits
Flash point: 103°F TCC

On DSL Inventory

Updated: January, 2010

All information, recommendations and suggestions, concerning the product and its use, are believed to be reliable. However, Nuplex Resins gives no assurance as to the accuracy, completeness, or adequacy for a particular purpose. It is the user's responsibility to determine the suitability for its own use of the products. No guarantee (whether expressed or implied) is made by Nuplex Resins as to the results to be obtained from using the described products, nor shall Nuplex Resins be liable for any use by others of the described products. Users are responsible for ensuring compliance with local legislation and obtaining the necessary certifications and authorizations. All orders are subject to the general conditions of sale of Nuplex Resins, which are printed overleaf and/or can be downloaded from www.nuplexresins.com. All of user's general terms and conditions are herewith deemed rejected. Nuplex Resins owns all copyrights and other intellectual property rights in the contents of this document. Reproduction or redistribution in any form is not allowed.