



TECHNICAL DATA SHEET

Setal 26-1688

A slightly branched polyester polyol
(European: Setal 168 SS-80)

General description:

Setal 26-1688 is a slightly branched polyester polyol with 4.3% hydroxyl functionality on non-volatile. This resin makes coatings with very good flexibility and durability when crosslinked with aliphatic polyisocyanates.

Technical features:

1. Flexible industrial topcoats where good chemical and solvent resistance is required
2. Flexibilizer for various 2K polyurethane paint systems

Suggested uses:

1. Topcoats for flexible substrates such as bumpers
2. As a flexibilizing additive or modifier for flexible coatings

Delivery form: 79% n.v. in n-butyl acetate / xylene (90 / 10 pbw)

Typical properties:

Property	Value	Units	Method *
Non-volatile, by wt.	79.0 ± 1.0	%	1A
Viscosity (Gardner)	1.3 – 3.5 (Y - Z1)	Pa.s	12B (SDM 2-1)
Color	150 maximum	APHA	8B
Acid value, as such	1.7 maximum	mg KOH/g	41A
Appearance	Clean, clear and free from extraneous matter		17A

* SBM: Nuplex Resins methods of determination (available on request).

Density: 9.20 ± 0.10 lbs./gal HEW on n.v. : 400
Flash point: 81°F Setafash
Non-volatile, by vol.: 75.1% *On DSL Inventory*

Updated: February, 2007

All information, recommendations and suggestions, concerning the product and its use, are believed to be reliable. However, Nuplex Resins gives no assurance as to the accuracy, completeness, or adequacy for a particular purpose. It is the user's responsibility to determine the suitability for its own use of the products. No guarantee (whether expressed or implied) is made by Nuplex Resins as to the results to be obtained from using the described products, nor shall Nuplex Resins be liable for any use by others of the described products. Users are responsible for ensuring compliance with local legislation and obtaining the necessary certifications and authorizations. All orders are subject to the general conditions of sale of Nuplex Resins, which are printed overleaf and/or can be downloaded from www.nuplexresins.com. All of user's general terms and conditions are herewith deemed rejected. Nuplex Resins owns all copyrights and other intellectual property rights in the contents of this document. Reproduction or redistribution in any form is not allowed.