



TECHNICAL DATA SHEET

SETAQUA 6766

An acrylic copolymer emulsion (37-6766)

General description:

SETAQUA 6766 is a self-cross linking acrylic copolymer emulsion intended for industrial air-dry interior and exterior pigmented and clear coatings. Coatings formulated with SETAQUA 6766 exhibit high gloss, good application properties, excellent blocking and chemical resistance.

Technical features:

1. High gloss with good coating appearance
2. Good application properties
3. Excellent blocking and chemical resistance properties

Suggested uses:

1. Clear topcoats and pigmented enamels
2. Air-dry coatings for interior and exterior pigmented finishes

Delivery form: 40% non-volatile in demineralized water

Typical properties

Property	Value	Units	Method *
Non-volatiles, by weight	40.0 ± 1.0	%	1 – 1
Viscosity	150 maximum	cps	2 – 2
pH value	8.5 – 9.5		8 – 1

*SDM: Nuplex Resins methods of determination (available on request)

Tg (theroretical):	50°C
Density:	8.70 lb/gal
Non-volatile, by vol.:	37.3%
Appearance:	Blue/white

On DSL Inventory

Updated: October, 2013

All information, recommendations and suggestions, concerning the product and its use, are believed to be reliable. However, Nuplex Resins gives no assurance as to the accuracy, completeness, or adequacy for a particular purpose. It is the user's responsibility to determine the suitability for its own use of the products. No guarantee (whether expressed or implied) is made by Nuplex Resins as to the results to be obtained from using the described products, nor shall Nuplex Resins be liable for any use by others of the described products. Users are responsible for ensuring compliance with local legislation and obtaining the necessary certifications and authorizations. All orders are subject to the general conditions of sale of Nuplex Resins, which are printed overleaf and/or can be downloaded from www.nuplexresins.com. All of user's general terms and conditions are herewith deemed rejected. Nuplex Resins owns all copyrights and other intellectual property rights in the contents of this document. Reproduction or redistribution in any form is not allowed.