



**NEW!** **PORAVER<sup>®</sup>**  
**SPECIAL BLEND**  
**0.25-0.5 mm & 0.5-1 mm**

ALL PURCHASE ORDERS FOR SUPERSACKS OF OUR SPECIAL BLEND WILL BE INVOICED AT THE INTRODUCTORY PRICE. VALID UNTIL DECEMBER 2018

PROPERTIES SPECIAL BLEND	STANDARD	PORAVER <sup>®</sup>
Grain sizes (ratio 50:50)	[mm]	0.25-0.5
	[mm]	0.5-1
Fineness modulus	ASTM C136	2.18
Dry loose bulk density	ASTM C9/C29M	20.1
Organic impurities	ASTM C40	no injurious compounds
Crush		455.4
Overgrain	EN 13055-1	0.4% by mass
Undergrain		5.9% by mass
The following data are valid for all grain sizes:		
pH value		9-12
Moisture content on delivery		≤ 0.5 %
Softening point		approx. 700 °C / 1300 °F
Color		creamy white
	[M]	54.28
Thermal conductivity	[W/m·K]	0.082
	[BTU-in/h·ft <sup>2</sup> ·°F]	0.569

**Promotion Details**

- Poraver grain size 0.25-0.5 mm & 0.5-1 mm
- New special blend ratio 50:50
- 1.4 cubic meter supersacks
- 950 lbs each
- Special price: \$0.30/lb

**USD \$285** each supersack

**Recommended Application Usage**

- Veneerstone mix
- Architectural precast
- Dry cast block manufacturing



For additional information please contact:  
**Traves W. Ogilvie**  
Sales Manager  
Eastern USA  
Phone: +1 401 636 0455  
Fax: +1 705 431 2701  
Email: togilvie@poraver.com