

**SID RICHARDSON**  
**CARBON COMPANY**

**SR311**

**Revision: 0**

**Date: 10/27/10S**

<u>Test Procedure</u>	<u>Typical Properties</u>	<u>Test Methods</u>
Oil Absorption Number, cc/100g	104 +/- 6	ASTM D2414
Iodine Adsorption, mg/g	82 +/- 5	ASTM D1510
Tint Strength, %	106 +/- 5	ASTM D3265
Sieve Residue, % max		
- No. 35	0.0005	ASTM D1514
- No. 325	0.0200	ASTM D1514

ASTM test methods were followed to produce this data and it is believed to be reliable and accurate; however, Sid Richardson does not guarantee a duplication of these results by others. For further information, please contact Sid Richardson Technical Service, 3560 W. Market Street., Akron, OH 44333, (330)-666-2777, Fax (330)-666-3015, email: jmcuppett@sidrich.com