

| <u>Test Procedure</u> | <u>Typical Properties</u> | <u>Test Methods</u> |
|--------------------------------|---------------------------|---------------------|
| Oil Absorption Number, cc/100g | 66 | ASTM D2414 |
| Iodine Adsorption, mg/g | 28 | ASTM D1510 |
| Tint Strength | 51 | ASTM D3265 |
| Heat Loss, % max (as shipped) | | |
| - Bag | 1.5 | ASTM D1509 |
| Sieve Residue, % max | | |
| - No. 35 | 0.0010 | ASTM D1514 |
| - No. 325 | 0.0250 | ASTM D1514 |