

SID RICHARDSON
CARBON COMPANY

SR750

Revision: 1

Date: 03/29/10S

<u>Test Procedure</u>	<u>Typical Properties</u>	<u>Test Methods</u>
Oil Absorption Number, cc/100g	65 +/- 5	ASTM D2414
Iodine Adsorption, mg/g	29 +/- 6	ASTM D1510
Tint Strength, %	58 +/- 4	ASTM D3265
Heat Loss, % max (as shipped)		
- Bulk	1.0	ASTM D1509
- Bag	1.0	ASTM D1509
Sieve Residue, % max		
- No. 35	0.0005	ASTM D1514
- No. 325	0.0200	ASTM D1514
Fines, 5', % max		
- Bulk	6.0	ASTM D1508
- Bag	9.0	ASTM D1508
Pellet Hardness, max		
- Maximum	65	ASTM D5230
- Average	35	ASTM D5230

ASTM test methods were followed to produce this data and it is believed to be reliable and accurate; however, Sid Richardson does not guarantee a duplication of these results by others. For further information, please contact Sid Richardson Technical Service, 3560 W. Market Street., Akron, OH 44333, (330)-666-2777, Fax (330)-666-3015, email: jmcuppett@sidrich.com