

VINNAPAS® 127 ED (VINNAPAS® WCP 67)

Product description

VINNAPAS® 127 ED (VINNAPAS® WCP 67) is a dispersion designed to improve the bond, tensile and flexural strengths of Portland cement based materials.

Properties

VINNAPAS® 127 ED (VINNAPAS® WCP 67) is a surfactant stabilized acrylic dispersion. It is produced without using solvent and/or plasticizer donors.

Special features

VINNAPAS® 127 ED (VINNAPAS® WCP 67) meets ASTM C 1059 - 86 requirements for Type II Non-redispersible Latex Bonding Agents.

Application

VINNAPAS® 127 ED (VINNAPAS® WCP 67) exhibits a high compatibility towards cement and its effect on cement setting is marginal. It can be used to formulate very workable and ductile mortars with very good adhesive properties, accompanied by a high cohesive strength. Therefore, this product can be used as an organic binder for cement mortars such as water proofing membranes, 2-component tile adhesive and concrete repair mortars.

VINNAPAS® 127 ED (VINNAPAS® WCP 67) offers a superior balance of adhesive /cohesive properties, which is advantageous in the use as general purpose primer.

VINNAPAS® 127 ED (VINNAPAS® WCP 67) can be used to improve the adhesion to various substrates like concrete, masonry, polystyrene and exterior sheathing. The impact resistance and the flexibility of a cementitious base coat is improved.

For typical application fields of VINNAPAS® 127 ED (VINNAPAS® WCP 67) you can refer to the following application table. Please discuss additional applications with your WACKER customer representative.

Application	Recommendation	Suitability
Cement admix	Mortars with improved adhesion	●
Tile adhesives	2-component tile adhesives	●
Concrete repair	Mortars with improved adhesion	●
Exterior Insulation & Finishing Systems (EIFS)	Adhesive mortars (2K)	●
	Base coats (2K)	●
Waterproofing membranes	Membranes with a high mechanical strength	●
Primers	General purpose primers	●
	Adhesion primers	●

● highly recommended ○ recommended

Storage

When the dispersion is stored in tanks, proper storage conditions must be maintained. VINNAPAS® 127 ED (VINNAPAS® WCP 67) has a shelf life of 6 months starting from the date of receipt if stored under cool (below 25 °C) but frost-free conditions in the original, unopened containers. Iron or galvanized iron containers and equipment are not recommended. Corrosion could result in discoloration of the dispersion or blends made from it in further processing. We therefore recommend the use of containers and equipment made of ceramic, rubberized or enameled materials, appropriately finished stainless steel, or plastic (rigid PVC, polyethylene or polyester resin).

Preservation for transport, storage and further processing

VINNAPAS® 127 ED (VINNAPAS® WCP 67) is adequately preserved during transportation and storage if kept in the original, unopened containers. When stored in tanks, the dispersion should be modified with a preservative to prevent microbial contamination. Suitable measures should be taken to ensure that the tanks are properly clean. In storage tanks in which the product is not stirred, it is advisable to cover the surface of the dispersion with 1 - 2 cm of water, to which a preservative has been added. This will prevent skin formation and microbial contamination. In the case of storage in silos, it is important that the air drawn into the silo when the

product is discharged is also kept free of germs. As a rule, all finished products manufactured from polymer dispersions also require preservation. The type and extent of preservation will depend on the raw materials used and the anticipated sources of contamination.

The compatibility and effectiveness of the preservatives should be checked for a given formulation. Preservative manufacturers will be able to advise you on the type and amount of conservation agent to use.

Packaging

Please contact Wacker Chemical Corporation for packaging and shipping information.

In case of industrial usage, please confirm delivery times. If larger amounts are required, please give advance notification.

For more commercial and technical information please contact a Wacker Chemical Corporation representative.

Wacker Chemical Corporation
6870 Tilghman Street
Allentown, PA 18106-9346
USA

Technical Center Allentown

Tel. +1 800 523-9476
Fax +1 517 264-4088
dispersions.customerservice@wacker.com

Additional information

If VINNAPAS® 127 ED (VINNAPAS® WCP 67) is used in applications other than those mentioned, the choice, processing and use of VINNAPAS® 127 ED (VINNAPAS® WCP 67) is the sole responsibility of the purchaser. All legal and other regulations must be complied with.

For questions concerning food contact status according to chapter 21 CFR (US FDA) and German BfR, please contact:

Wacker Chemie AG
Hanns-Seidel-Platz 4
D-81737 Munich
Germany

Safety notes

Comprehensive instructions are given in the appropriate material safety data sheets. These are available on request from WACKER sales offices.

Product data

Specification data	Inspection Method	Value
Solids content	specific method	46 - 48 %
Viscosity, dynamic at 23 °C	BROOKFIELD	< 100 mPa.s
pH-Value	ASTM E 70	9.0 - 10.0

Typical general characteristics	Inspection Method	Value
Minimum film forming temperature	specific method	approx. 12 °C
Predominant particle size	specific method	approx. 300 nm
Protective colloid / emulsifier system	specific method	surfactants
Compatibility with cement	specific method	very good
Appearance of the dispersion film	Visual	clear
Glass transition temperature	ASTM D 3418	approx. 7 °C

These figures are only intended as a guide and should not be used in preparing specifications.

The data presented in this leaflet are in accordance with the present state of our knowledge, but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this leaflet should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are also being used. The recommendations do not absolve the user from the obligation of investigating the possibility of infringement of third parties' rights and, if necessary, clarifying the position. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the products for a particular purpose.

The management system has been certified according to DIN EN ISO 9001 and DIN EN ISO 14001

WACKER is a trademark of Wacker Chemie AG.
VINNAPAS® is a trademark of Wacker Chemical Corporation.

For technical, quality, or product safety questions, please contact:

Wacker Chemical Corporation
3301 Sutton Road
Adrian, Michigan 49221-9397, USA