

Hydroxyl functionalited polyacrylic dispersion

## Technical Data Sheet

Name: Antkote® 2030  
Revision Date: 2017-12-22

NO.IC\_081  
Version: 1.1

### Product Description

Antkote® 2030 is a hydroxyl functionalited polyacrylic dispersion designed for waterborne one component baking coatings in combination with amino resins or blocked polyisocyanates. Approx. 44% in water/2-butoxyethanol, neutralized with 2-dimethylethanolamine, approx. 47.7:7:1.3. It also can be used for waterborne two-component coatings in combination with polyisocyanates.

### Properties

1. High gloss (20°) over 80.
2. Excellent mechanical stability.

### Characteristic data\*

Property	Value	Unit	Method
Appearance	Milky white		
Weight Solids	42.0-44.0	%	WHPU/T 011-571-2017
pH	7.0-9.0		GB 6920-1986
Viscosity	2000-10000	mPa·s	Brookfield,LV,64#,60rpm,25°C
OH content	3.0	%	
Density	1.06	g/cm <sup>3</sup>	GB/T4472-2011

\* Property values represent typical results only and are not to be considered as specifications, subject to specific COA

### Storage

The product should be stored in dry conditions above 5°C and below 35°C with the integrity of the packaging, and prevent direct sunlight. The validity of this product is for 6 months, performance assessment is recommended before use after more than 6 months. The product should be protected from freezing during storage. Using it up is suggested once opened.

# Antkote<sup>®</sup> 2030



**Disclaimer:** Wanhua Chemical Group Co., LTD. recommends that any customers of this material should check with Materials Safety Data Sheet (MSDS) for details about safely handling this material. We also suggest that you contact the suppliers of any other materials used in our recommended formulations and suggestions for appropriate health and safety regulations prior to use. The information contained herein is believed to be reliable. However, nothing in this technical sheet should be considered as a representation of warranty, express or implicit, regarding the product characteristics, application, quality, safety, merchantability or fitness for a particular purpose. Nothing contained herein is to be considered as permission, recommendation, nor as an inducement to practice any patented invention without permission of the patent owner.