

Acrylic copolymer emulsion

## Technical Data Sheet

Name: Lacper<sup>®</sup>4502  
Revision Date: 2017-12-26

NO. WHSM\_4502  
Version: 1.1

### Product Description

Lacper<sup>®</sup> 4502 is an anionic acrylic emulsion designed for wood coatings and can be used as both primer and topcoat. It has excellent film forming properties, chemical resistance, sandability and low odor. It does not contain alkyl phenyl ethoxylate (APEO) or ammonia. Biocide: CMIT/MIT 3:1 10ppm, and MIT 200ppm.

### Properties

1. Film forming properties, low odor
2. Good sandability
3. chemical resistance
4. Good stackability

### Characteristic data\*

Property	Value	Unit	Method
Appearance	Translucent to milky white		
Weight Solids	44-46	wt%	WHPU/T011-571-2017
pH	7.0-9.0		GB 6920-1986
MFFT	21	°C	GB/T 9267-2008
Viscosity	10~500	mPa·s	GB/T 2794-2013

\*Property values represent typical results only and are not to be considered as specifications, subject to specific COA

### Storage

The product should be stored in dry conditions above 5°C and below 35°C with the integrity of the packaging, and prevent direct sunlight. The validity of this product is for 12 months, performance assessment is recommended before use after more than 12 months. The product should be protected from freezing during storage. After opening the packing, suggested to use up one time.

Well filtration before using is necessary as normal water based binder.

# Lacper<sup>®</sup>4502



**Disclaimer:** Wanhua Chemical Group Co., LTD. recommends that any customers of this material should check with Materials Safety Data Sheet (MSDS) for details about safely handling this material. We also suggest that you contact the suppliers of any other materials used in our recommended formulations and suggestions for appropriate health and safety regulations prior to use. The information contained herein is believed to be reliable. However, nothing in this technical sheet should be considered as a representation of warranty, express or implicit, regarding the product characteristics, application, quality, safety, merchantability or fitness for a particular purpose. Nothing contained herein is to be considered as permission, recommendation, nor as an inducement to practice any patented invention without permission of the patent owner.