

Hydrophobic Modified Ethoxylated Urethane

## Technical Data Sheet

Name: Vesmody® U601  
Revision Date: 2018-01-11

NO.AA\_008  
Version: 1.1

### Product Description

**Vesmody® U601** a nonionic urethane rheology modifier, a suitable thickening agent for any waterborne painting system, especially for adhesive, as well as industry coating and architectural coating. Vesmody® U601 is an efficient pseudoplastic PU thickener with well-balanced efficiency in medium and low shear range, allows the formulation of paints with an excellent balance between flow and sag. Vesmody® U601 is environmentally friendly, low VOC, ultra-low odor, free of alkylphenol ethoxylate (APEO), tin compound and any organic solvent. Solvent: water. Biocide: (CMIT/MIT = 3:1) 10 ppm, MIT 200 ppm.

### Properties

1. Tin-free, Solvent-free, Apeo free
2. Ultra-Low odor, low VOC
3. Excellent thickening efficiency
4. Good balance between low and medium shear viscosity
5. Excellent leveling and sag resistance
6. Use over a wide pH range

### Characteristic data\*

Property	Value	Unit	Method
<b>Appearance</b>	Translucent to slightly milky-white liquid		
<b>Weight Solids</b>	34-36	%	WHPU/T011-571-2017 (4cm,150°C,20min)
<b>Active solids content</b>	19-21	%	
<b>pH</b>	6.0-7.0		GB 6920-1986, 25°C
<b>Viscosity</b>	30000-38000	mPa·s	Brookfield RV, 5#/6rpm, 25°C

# Vesmody® U601



---

Density	1.04	g/cm <sup>3</sup>	GB/T 4472-2011, 25°C
Chemistry	HEUR		

---

\*These properties are typical but do not constitute specifications.

## Instructions for use

**Vesmody® U601** is supplied as a pourable liquid, it is easy to use and can be added in any formulation time directly or after dilution. Depending on the character and amount of the emulsion as well as filler and pigment, the amount of the addition is variable, probably 0.2-3.0% by weight of the formulation in its supplied form. The exact amount required in each formulation should be determined by pre-trials.

## Storage

The product should be stored in dry conditions above 5°C and below 35°C with the integrity of the packaging, and prevent direct sunlight. The validity of this product is for 12 months, performance assessment is recommended before use after shelf life. The product should be protected from freezing during storage. After opening the packing, suggested to use up one time.

**Disclaimer:** Wanhua Chemical Group Co., LTD. recommends that any customers of this material should check with Materials Safety Data Sheet (MSDS) for details about safely handling this material. We also suggest that you contact the suppliers of any other materials used in our recommended formulations and suggestions for appropriate health and safety regulations prior to use. The information contained herein is believed to be reliable. However, nothing in this technical sheet should be considered as a representation of warranty, express or implicit, regarding the product characteristics, application, quality, safety, merchantability or fitness for a particular purpose. Nothing contained herein is to be considered as permission, recommendation, nor as an inducement to practice any patented invention without permission of the patent owner.