

## Technical Data Sheet

Revision Date: 2017-06-30  
Name: WANNATE<sup>®</sup> PM-200S

NO. WHPU\_0020  
Version: 6.0

### Application

WANNATE<sup>®</sup> PM-200S is a diisocyanate-diphenylmethane(MDI)-based composition containing some higher functionality isocyanates. It is a brown liquid at ambient temperatures.

WANNATE<sup>®</sup> PM-200S can be widely used in the production of rigid PU foam heat-insulating materials; also used in isocyanurate foam, paints, adhesives, structural foam, cellular integral skin foam, automotive bumper and interior parts, high-resilience foam and synthetic wood, etc. Due to its unique composition structure, WANNATE<sup>®</sup> PM-200S can provide lower reactivity and better flow ability. It is, therefore, particularly suitable for the production which require strict flow ability of systems.

### Typical Physical and Chemical Properties

Item(s)	Specifications
Appearance	Brown Liquid
Viscosity(25°C)/ ( mPa • s )	150~250
NCO Content/%	30.8~32.0
Density (25°C) / ( g/cm <sup>3</sup> )	1.220~1.250
Acid Content/%	≤0.030
Hydrolysable Chlorine/%	≤0.20

### Package(s)

210L iron drums, 250kg/drum

### Storage

Since WANNATE<sup>®</sup> PM-200S is a reactive chemical, reaction with atmospheric moisture happens easily and leads to the formation of insoluble ureas and carbon dioxide gas, which can result in pressure build-up in closed containers and viscosity increase of the product. Containers must therefore be absolutely dry and carefully sealed after congested with nitrogen.

Containers of WANNATE<sup>®</sup> PM-200S should be kept properly closed and stored indoors at ambient temperature (15-35°C) in a well-ventilated area. Storage at low temperature (below

5°C) may lead to some crystallization; this material must, therefore, be protected from frost. If crystallization does occur, the material should be heated by rolling the drum in a hot air oven at 70-80°C to melt it out, and should then be thoroughly agitated before use. Melting in a water bath is not recommended.

Extended storage at temperatures above 50°C is not recommended to prevent from the formation of insoluble solids and viscosity increase.

### **Shelf Life**

Under recommended storage conditions, the shelf life of WANNATE<sup>®</sup> PM-200S is one year since the date of production.

**For more information about safety and environment, please refer to our SDS or contact our customer service center.**

### **Version information:**

Date of first issue : June 6 ,2013

Date of 1<sup>st</sup> revise: Feb 6, 2015 Reason for revision : The need of product classification

Date of 2<sup>nd</sup> revise : May 5, 2015 Reason for revision: A change of company address

Date of 3<sup>rd</sup> revise : Aug.18, 2015 Reason for revision: Unified the template of TDS

Date of 4<sup>th</sup> revise: May 31, 2016 Reason for revision: Change of product standard.

Date of 5<sup>th</sup> revise: June 30, 2017 Reason for revision: Change of company LOGO.

---

### **For further information please contact us:**

Address: Wanhua Chemical Group Co., Ltd.

No.17,Tianshan Rd,YEDA,Yantai,264006,China

Customer service: Tel: +86 (535) 3388000 Fax: +86 (535) 683 7242

Web-site: <http://www.whchem.com>

The information provided here is for reference only. The specification will be provided in the quality certificate or in the contract. It is the user's responsibility to test the material and its suitability for a process. We have no control over what another party does with the material and we cannot take any responsibility for another party's action. Nor will we be responsible for any indirect damages while using our products. The user is welcome to contact our customer and technical service center with questions on our products.